

Technical Data Sheet

Petrothene LB560201

High Density Polyethylene

Product Description

Petrothene LB560201 is a high density polyethylene resin that exhibits good stiffness and environmental stress crack resistance. Typical applications include bottles for household chemicals such as bleach, cleaners and detergents.

Regulatory Status

For regulatory compliance information, see *Petrothene* LB560201 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Bottles For Consumer Goods; Bottles for Industrial Use
Market	Rigid Packaging
Processing Method	Extrusion Blow Molding

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	0.30	g/10 min	0.30	g/10 min	ASTM D1238
Density, (23 °C)	0.952	g/cm ³	0.952	g/cm ³	ASTM D1505
Mechanical					
Flexural Modulus, (1% Secant)	185000	psi	1280	MPa	ASTM D790
Tensile Strength at Yield	3960	psi	27.3	MPa	ASTM D638
Tensile Elongation at Break	>600	%	>600	%	ASTM D638
Environmental Stress Crack Resistance, F ₅₀ (100% Igepal®, Cond B)	35	hr	35	hr	ASTM D1693
Impact					
Tensile Impact Strength	120	ft-lb/in ²	252	kJ/m ²	ASTM D1822
Hardness					
Shore Hardness, (Shore D)	66		66		ASTM D2240
Thermal					
Vicat Softening Temperature	253	°F	123	°C	ASTM D1525
Low Temperature Brittleness, F ₅₀	<-105	°F	<-76	°C	ASTM D746
Deflection Temperature Under Load, (66 psi, Unannealed)	167	°F	75	°C	ASTM D648