

## Technical Data Sheet

**Petrothene LR732011**

High Density Polyethylene

**Product Description**

*Petrothene LR732011* exhibits exceptional processability when used in a variety of different blowmolding processes. Finished articles made from this resin show an excellent balance of stiffness and environmental stress crack resistance. Typical applications include containers for bleach, detergent, household chemicals and personal care products. This product contains synthetic antistat.

**Regulatory Status**

For regulatory compliance information, see *Petrothene LR732011* [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

<b>Status</b>	Commercial: Active
<b>Availability</b>	North America
<b>Application</b>	Bottles For Consumer Goods
<b>Market</b>	Rigid Packaging
<b>Processing Method</b>	Extrusion Blow Molding
<b>Attribute</b>	Contains Antistat; Excellent Processability

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
<b>Physical</b>					
Melt Flow Rate, (190 °C/2.16 kg)	0.30	g/10 min	0.30	g/10 min	ASTM D1238
Density, (23 °C)	0.953	g/cm <sup>3</sup>	0.953	g/cm <sup>3</sup>	ASTM D1505
<b>Mechanical</b>					
Flexural Modulus, (1% Secant)	181000	psi	1250	MPa	ASTM D790
Tensile Strength at Yield	4000	psi	27.6	MPa	ASTM D638
Tensile Elongation at Break	>500	%	>500	%	ASTM D638
Environmental Stress Crack Resistance, F <sub>50</sub> (100% Igepal®, Cond B)	30	hr	30	hr	ASTM D1693
<b>Impact</b>					
Tensile Impact Strength	128	ft-lb/in <sup>2</sup>	269	kJ/m <sup>2</sup>	ASTM D1822
<b>Hardness</b>					
Shore Hardness, (Shore D)	67		67		ASTM D2240
<b>Thermal</b>					
Vicat Softening Temperature	259	°F	126	°C	ASTM D1525
Low Temperature Brittleness, F <sub>50</sub>	<-105	°F	<-76	°C	ASTM D746
Deflection Temperature Under Load, (66 psi, Unannealed)	167	°F	75	°C	ASTM D648