

Technical Data Sheet

Lupolen 3026K



Low Density Polyethylene

Product Description

Lupolen 3026 K is an additivated, low density polyethylene. It contains slip and anti-blocking agent. It is characterized by a good processability.

LyondellBasell customers report that films made from *Lupolen 3026 K* exhibit a glossy surface finish.

Lupolen 3026 K provides the option to produce films with very good optical properties.

It is delivered in pellet form.

This product is not intended for use in medical and pharmaceutical applications.

Regulatory Status

For regulatory compliance information, see *Lupolen 3026K* [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Europe
Application	Food Packaging Film; Lamination Film; Shrink Film
Market	Flexible Packaging
Processing Method	Blown Film; Cast Film
Attribute	Good Heat Seal; Good Processability; Low Friction; Superior Optical Properties; Unspecified Antiblocking; Unspecified Slip

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (190 °C/2.16 kg)	4.0	g/10 min	ISO 1133-1
Density	0.928	g/cm ³	ISO 1183-1
Mechanical			
Tensile Modulus	300	MPa	ISO 527-1, -2
Tensile Stress at Yield	13	MPa	ISO 527-1, -2
Film			
Dart Drop Impact Strength, F50	90	g	ASTM D1709
Tensile Strength			
MD	20	MPa	ISO 527-1, -3
TD	15	MPa	ISO 527-1, -3
Tensile Strain at Break			
MD	300	%	ISO 527-1, -3
TD	550	%	ISO 527-1, -3
Coefficient of Friction	<0.2		ISO 8295
Impact			
Failure Energy	3.5	J/mm	DIN 53373
Thermal			
Vicat Softening Temperature, (A/50 N)	97	°C	ISO 306
Peak Melting Point	114	°C	ISO 11357-3

Optical

Haze, (50 μm)	<8 %	ASTM D1003
Gloss		
(20°)	>70	ASTM D2457
(60°)	>110	ASTM D2457

Additive

Slip, Erucamide	700 ppm	LYB Method
Antiblock, Natural Silica	1000 ppm	ISO 3451-1

Additional Information

Test Specimen

Film properties tested using 50 μm thickness blown film extruded at a melt temperature of 170°C and a blow-up ratio of 2.5:1.

Processing Parameters

Extrusion Temperature	150-190 °C
-----------------------	------------

Notes

These are typical property values not to be construed as specification limits.