

Microthene G

# MN71400


Low Density Polyethylene  
Ground Polyolefin Powder

Melt Index: 70 Density: 0.912



## General Description

*Microthene G* polyolefin powders are ground, irregularly-shaped particles for use in a broad range of specialty applications. *Microthene G* powders combine the unique properties of a polyolefin resin with a small ground particle size.



## Regulatory Status

MN71400 meets the requirements of the Food and Drug Administration, 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "...articles or components of articles intended for use in contact with food..." Specific limitations or conditions of use may apply. Contact your Equistar product safety representative for more information.

## Processing Techniques

The small size and irregular shape of *Microthene G* powders facilitate dispersion with other components. Specific suggestions can be made only when equipment, materials, process parameters and conditions of use are known.

## Typical Properties

Polymer Property	Nominal Value	Units	Test Method
Melt Index	70	g/10 min	ASTM D1238
Density	0.912	g/cc	ASTM D1505
Vicat Softening Point	75.6 / 168.1	°C/°F	ASTM D1525
Peak Melting Point	100.8 / 213.4	°C/°F	ASTM D3418
Low Temperature Brittleness	-22.7 / -8.9	°C/°F	ASTM D746
Tensile Strength @ Break	7.7 / 1,100	MPa/psi	ASTM D638
Elongation @ Break	400	%	ASTM D638
Flexural Modulus	186 / 27,000	MPa/psi	ASTM D790
Hardness, Shore D	51 / 44	max / 15 sec	ASTM D2240
<b>Powder Property</b>			
Particle Shape	Irregular		
Average Particle Size	50	mesh	ETM RoTap Sieve Analysis*

\* ETM = Equistar Test Method

These are typical values not to be construed as specification limits.