

Technical Data Sheet

Petrothene NA952094

Low Density Polyethylene

Product Description

Petrothene NA952094 is a low density homopolymer resin selected by customers for use in industrial and consumer packaging as well as liner and bag applications. NA952094 has an excellent balance of processability, toughness and drawdown.

Application	Agriculture Film; Bags & Pouches; Can Liners; Film Wrap; Food Packaging Film; Lamination Film; Liner Film; Secondary Packaging; Surface Protection Film
Market	Flexible Packaging
Processing Method	Blown Film; Cast Film

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	2.0	g/10 min	2.0	g/10 min	ASTM D1238
Base Resin Density, (23 °C)	0.919	g/cm ³	0.919	g/cm ³	ASTM D1505
Product Density, (23 °C)	0.921	g/cm ³	0.921	g/cm ³	ASTM D1505
Mechanical					
Tensile Strength	1800	psi	12.4	MPa	ASTM D638
Tensile Elongation at Break	650	%	650	%	ASTM D638
Film					
Dart Drop Impact Strength, F50	110	g	110	g	ASTM D1709
Tensile Strength at Break					
MD	3200	psi	22.1	MPa	ASTM D882
TD	2300	psi	15.9	MPa	ASTM D882
Tensile Elongation at Break					
MD	200	%	200	%	ASTM D882
TD	500	%	500	%	ASTM D882
1% Secant Modulus					
MD	26500	psi	183	MPa	ASTM D882
TD	32000	psi	221	MPa	ASTM D882
Elmendorf Tear Strength					
MD	350	g	350	g	ASTM D1922
TD	70	g	70	g	ASTM D1922
Thermal					
Vicat Softening Temperature	185	°F	85	°C	ASTM D1525
Additive					
Slip	500	ppm	500	ppm	LYB Method
Antiblock	4000	ppm	4000	ppm	LYB Method