

Technical Data Sheet

Petrothene NA980000

Low Density Polyethylene

Product Description

Petrothene NA980000 is a low density homopolymer resin selected by customers for use in shrink packaging, bundling, pallet wrap and heavy-duty liner applications. NA980000 is also selected by customers for use in blow molding squeeze bottles and other specialty applications. Excellent bubble stability, melt strength, impact and shrinkage are key attributes of NA980000.

Application	Agriculture Film; Bags & Pouches; Bottles and Vials; Bottles For Consumer Goods; Bottles for Industrial Use; Can Liners; Clear Containers; Film Wrap; Food Packaging Film; Heavy Duty Packaging; Liner Film; Opaque Containers; Shrink Film; Specialty Film; Textile Packaging Film
Market	Flexible Packaging; Rigid Packaging
Processing Method	Blown Film; Extrusion Blow Molding

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	0.25	g/10 min	0.25	g/10 min	ASTM D1238
Base Resin Density, (23 °C)	0.920	g/cm ³	0.920	g/cm ³	ASTM D1505
Product Density, (23 °C)	0.920	g/cm ³	0.920	g/cm ³	ASTM D1505
Mechanical					
Tensile Strength at Break	2600	psi	17.9	MPa	ASTM D638
Tensile Strength at Yield	1420	psi	9.79	MPa	ASTM D638
Tensile Elongation at Break	700	%	700	%	ASTM D638
Tensile Elongation at Yield	100	%	100	%	ASTM D638
Film					
Dart Drop Impact Strength, F50	180	g	180	g	ASTM D1709
Tensile Strength at Break					
MD	3000	psi	20.7	MPa	ASTM D882
TD	2800	psi	19.3	MPa	ASTM D882
Tensile Elongation at Break					
MD	310	%	310	%	ASTM D882
TD	430	%	430	%	ASTM D882
1% Secant Modulus					
MD	30000	psi	207	MPa	ASTM D882
TD	35000	psi	241	MPa	ASTM D882
Hardness					
Shore Hardness, (Shore D)	45		45		ASTM D2240
Thermal					
Vicat Softening Temperature	199	°F	93	°C	ASTM D1525
Low Temperature Brittleness, F ₅₀	-103	°F	-75	°C	ASTM D746
Additive					
Slip	None		None		LYB Method
Antiblock	None		None		LYB Method