

## Technical Data Sheet

### *lcorene* 3575 RED 4756



Linear Low Density Polyethylene

#### Product Description

*lcorene* 3575 is a hexene linear low density polyethylene with outstanding processability, specifically developed for rotational moulding. This grade is suitable for use in general purpose applications. It has a good balance of properties such as toughness, easy flow and stiffness. *lcorene* 3575 is WRAS approved: 1612553

|                          |  |
|--------------------------|--|
| <b>Processing Method</b> | Rotomolding  |
| <b>Attribute</b>         | Good Processability; Good Stiffness; Good Toughness; High Flow; UV Resistant |
| <b>Forms</b>             | Powder   |
| <b>Appearance</b>        | Natural Color; Unspecified Color   |
| <b>Additive</b>          | UV Stabilizer  |
| <b>Application</b>       | Containers; General Purpose  |

| Typical Properties                                | Nominal Value | Units             | Test Method |
|---|---------------|-------------------|-------------|
| <b>Physical</b>                                   |               |                   |             |
| Melt Flow Rate, (190 °C/2.16 kg)                  | 7.0           | g/10 min          | ASTM D1238  |
| Density   | 0.935         | g/cm <sup>3</sup> | ASTM D1505  |
| <b>Mechanical</b>                                 |               |                   |             |
| Tensile Strength at Yield                         | 17.0          | MPa               | ISO 527     |
| Flexural Modulus                                  | 650           | MPa               | ISO 178     |
| Tensile Elongation at Break                       | >450          | %                 | ASTM D638   |
| <b>Impact</b>                                     |               |                   |             |
| Drop Impact Resistance, (-20 °C, Internal Method) | 170           | J/cm              | ASTM D4226  |
| <b>Hardness</b>                                   |               |                   |             |
| Durometer Hardness, (Shore D)                     | 55            |                   | ASTM D2240  |
| <b>Thermal</b>                                    |               |                   |             |
| Vicat Softening Temperature                       | 115           | °C                | ISO 306     |
| Melting Temperature                               | 127           | °C                | DSC         |