

Technical Data Sheet

Microthene MP564189

Linear Low Density Polyethylene

Product Description

Microthene MP564189 exhibits good stiffness and low temperature toughness. Typical applications include trash cans, industrial containers, housewares and toys. MP564189 is 16 mesh powder and is also available in pellet form *Petrothene* GA564189.

Market Rigid Packaging

Processing Method Injection Molding

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	20	g/10 min	20	g/10 min	ASTM D1238
Density, (23 °C)	0.924	g/cm ³	0.924	g/cm ³	ASTM D1505
Spiral Flow	12.6	in	32.1	cm	LYB Method
Mechanical					
Flexural Modulus					
(1% Secant)	63000	psi	440	MPa	ASTM D790
(2% Secant)	55000	psi	380	MPa	ASTM D790
Tensile Strength at Break, (23 °C)	1200	psi	8	MPa	ASTM D638
Tensile Strength at Yield, (23 °C)	2100	psi	14	MPa	ASTM D638
Tensile Elongation at Yield, (23 °C)	12	%	12	%	ASTM D638
Hardness					
Shore Hardness, (Shore D)	57		57		ASTM D2240
Thermal					
Vicat Softening Temperature	196	°F	91	°C	ASTM D1525
Low Temperature Brittleness, F ₅₀	<-105	°F	<-76	°C	ASTM D746
Deflection Temperature Under Load, (66 psi, Unannealed)	113	°F	45	°C	ASTM D648