

## Technical Data Sheet

# Polylox (MABS) Typ C2

Methyl Methacrylate / ABS  
LyondellBasell Industries  
Engineering Plastics

### Product Description

good flow transparent MABS grade

### General

Appearance	• Clear/Transparent
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• MABS

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.09 g/cm <sup>3</sup>	1.09 g/cm <sup>3</sup>	ISO 1183/A
Melt Volume-Flow Rate (MVR) (220°C/10.0 Kg)	18 cm <sup>3</sup> /10min	18 cm <sup>3</sup> /10min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	276000 psi	1900 MPa	ISO 527-1/1A/1
Tensile Stress (Yield)	6380 psi	44.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	3.5 %	3.5 %	ISO 527-2/1A/50
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	4.3 ft·lb/in <sup>2</sup>	9.0 kJ/m <sup>2</sup>	
73°F (23°C)	7.6 ft·lb/in <sup>2</sup>	16 kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	30 ft·lb/in <sup>2</sup>	62 kJ/m <sup>2</sup>	
73°F (23°C)	38 ft·lb/in <sup>2</sup>	79 kJ/m <sup>2</sup>	
Notched Izod Impact Strength (73°F (23°C))	8.1 ft·lb/in <sup>2</sup>	17 kJ/m <sup>2</sup>	ISO 180/4A
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness (H 358/30)	13900 psi	96.0 MPa	ISO 2039-1
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	198 °F	92.0 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	174 °F	79.0 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	199 °F	93.0 °C	ISO 306/B50
--	217 °F	103 °C	ISO 306/A50
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 In (1.6 Mm)	HB	HB	
Glow Wire Flammability Index			IEC 60695-2-12
0.06 In (1.5 Mm)	1250 °F	675 °C	
0.12 In (3.0 Mm)	1250 °F	675 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 In (1.5 Mm)	1290 °F	700 °C	
0.12 In (3.0 Mm)	1290 °F	700 °C	

### Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Technical Data Sheet

# Polylux (MABS) Typ C2

Methyl Methacrylate / ABS  
 LyondellBasell Industries  
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	158 °F	70 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Processing (Melt) Temp	392 to 464 °F	200 to 240 °C
Mold Temperature	104 to 176 °F	40 to 80 °C

**Notes**

These are typical property values not to be construed as specification limits.