

## Technical Data Sheet

### Alcryn ALC - 4670NCNAT



Melt Processable Rubber

#### Product Description

Alcryn® 4670 NC is a Melt Processable Rubber (MPR) product. It can be processed by blow molding, calendaring, compression molding, or extrusion and is available in Asia Pacific, Europe, or North America. Applications of Alcryn® 4670 NC include engineering/industrial parts, hose/tubing, wire & cable, fabrics/fibers and handles.

|                          |   |
|--------------------------|---|
| <b>Processing Method</b> | Blow Molding; Calendaring; Compression Molding; Extrusion; Vacuum Forming   |
| <b>Attribute</b>         | Fast Molding Cycle; High Heat Resistance; Noise Damping; Oil Resistant; Ozone Resistant; Recyclable Material; Vibration Damping   |
| <b>Forms</b>             | Pellets   |
| <b>Appearance</b>        | Natural Color   |
| <b>Application</b>       | Cable Jacketing; Coating Applications; Fabric Coatings; Flexible Grips; Gaskets; General Purpose; Handles; Hose; Overmolding; Profiles; Seals; Tubing; Weatherstripping; Wire & Cable |

| Typical Properties                                     | Nominal Value | English Units     | Nominal Value | SI Units          | Test Method |
|--|---------------|-------------------|---------------|-------------------|-------------|
| <b>Physical</b>  |               |                   |               |                   |             |
| Density  | 1.25          | g/cm <sup>3</sup> | 1.25          | g/cm <sup>3</sup> | ISO 1183    |
| Change in Volume                                       |               |                   |               |                   |             |
| (in ASTM #1 Oil, 100 °C, 168 hr)                       | -17           | %                 | -17           | %                 | ASTM D471   |
| (in Water, 100 °C, 168 hr)                             | 11            | %                 | 11            | %                 | ASTM D471   |
| (in Reference Fuel B, 24 °C, 168 hr)                   | 16            | %                 | 16            | %                 | ASTM D471   |
| (in ASTM #3 Oil, 100 °C, 168 hr)                       | 17            | %                 | 17            | %                 | ASTM D471   |
| Melt Viscosity, (190 °C, 300 sec <sup>-1</sup> )       |               |                   | 500           | Pa·s              | ASTM D3835  |
| <b>Mechanical</b>                                      |               |                   |               |                   |             |
| Tensile Modulus, (23 °C)                               | 570           | psi               |               |                   | ASTM D638   |
| Tensile Strength at Yield, (2 in/min)                  | 1280          | psi               |               |                   | ASTM D638   |
| (.0750 in. Compression Molded)                         |               |                   |               |                   |             |
| Tensile Elongation at Break, (23 °C)                   | 440           | %                 | 440           | %                 | ASTM D638   |
| (.0750 in. Compression Molded)                         |               |                   |               |                   |             |
| Change in Ultimate Elongation in Air, (121 °C, 168 hr) | 380           | %                 | 380           | %                 | ASTM D471   |
| Torsion Modulus  |               |                   |               |                   |             |
| (24 °C, 1.9 mm)  | 350           | psi               |               |                   | ASTM D1043  |
| (-20 °C, 1.9 mm)                                       | 4000          | psi               |               |                   | ASTM D1043  |
| Tensile Set  | 9             | %                 | 9             | %                 | ASTM D412   |
| Clash-Berg Modulus, (-21 °C)                           |               |                   | 68.9          | MPa               | ASTM D1043  |
| Tear Strength  |               |                   | 38.5          | kN/m              | ASTM D624   |

| <b>Hardness</b>  |      |               |               |               |          |
|--|------|---------------|---------------|---------------|----------|
| Shore Hardness, (Shore A, 15 sec)                              | 70   | 70            | ASTM D2240    |               |          |
| Change in Shore Hardness in Air, (Shore A, 125 °C, 168 hr)     | 64   | 64            | ISO 188       |               |          |
| Change in Durometer Hardness in Air, (Shore A, 125 °C, 168 hr) | 64   | 64            | ASTM D471     |               |          |
| <b>Thermal</b>   |      |               |               |               |          |
| Low Temperature Brittleness                                    |      | -60 °C        | ASTM D746     |               |          |
| <b>Additional Information</b>                                  |      |               |               |               |          |
| Compression Set  |      |               |               |               |          |
| (24 °C, 22 hr, Method B)                                       | 21 % | 21 %          | ASTM D395 B   |               |          |
| (100 °C, 22 hr, Method B)                                      | 74 % | 74 %          | ASTM D395 B   |               |          |
| <b>Extrusion Parameters</b>                                    |      | Nominal Value | English Units | Nominal Value | SI Units |
| Melt Temperature   |      |               |               | 177           | °C       |