

Technical Data Sheet

Alcryn Alcryn 2250 BK

Melt Processable Rubber
LyondellBasell Industries
Engineering Plastics

General			
Features	<ul style="list-style-type: none"> Fast Molding Cycle General Purpose High Flow 	<ul style="list-style-type: none"> High Heat Resistance Noise Damping Oil Resistant 	<ul style="list-style-type: none"> Ozone Resistant Recyclable Material Vibration Damping
Uses	<ul style="list-style-type: none"> Cable Jacketing Coating Applications Fabric Coatings Flexible Grips Gaskets 	<ul style="list-style-type: none"> General Purpose Handles Hose Overmolding Profiles 	<ul style="list-style-type: none"> Seals Tubing Weatherstripping Wire & Cable Applications
RoHS Compliance	<ul style="list-style-type: none"> RoHS Compliant 		
Appearance	<ul style="list-style-type: none"> Translucent 		
Forms	<ul style="list-style-type: none"> Pellets 		
Processing Method	<ul style="list-style-type: none"> Blow Molding Extrusion 	<ul style="list-style-type: none"> Injection Molding Vacuum Forming 	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity			
--	1.06	1.06 g/cm ³	ASTM D471
--	1.06 g/cm ³	1.06 g/cm ³	ISO 2781

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Taber Abrasion Resistance			ASTM D1044
1000 Cycles, 1000 G, Cs-17 Wheel	5.00 mg	5.00 mg	
Torsion Modulus ¹			ASTM D1043
-4°f (-20°c), 74.8 Mil (1.90 Mm)	410 psi	2.83 MPa	
75°f (24°c), 74.8 Mil (1.90 Mm)	300 psi	2.07 MPa	

Elastomers	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Set ²	7 %	7 %	ASTM D412
Tensile Stress			
100% Strain, 0.0748 In (1.90 Mm) ¹	300 psi	2.07 MPa	ASTM D412
100% Strain, 257°f (125°c), 0.0748 In (1.90 Mm) ³	232 psi	1.60 MPa	ASTM D573 ISO 188
100% Strain, 0.0748 In (1.90 Mm) ¹	276 psi	1.90 MPa	ISO 37
Tensile Strength			
Yield, 0.0748 In (1.90 Mm) ¹	1010 psi	6.96 MPa	ASTM D412
Yield, 257°f (125°c), 0.0748 In (1.90 Mm) ³	928 psi	6.40 MPa	ASTM D573 ISO 188
Yield, 0.0748 In (1.90 Mm) ¹	986 psi	6.80 MPa	ISO 37
Tensile Elongation			
Break, 0.0748 In (1.90 Mm) ¹	430 %	430 %	ASTM D412
Break, 257°f (125°c), 0.0748 In (1.90 Mm) ³	430 %	430 %	ASTM D573
Break, 0.0748 In (1.90 Mm) ¹	420 %	420 %	ISO 37
Break, 257°f (125°c), 0.0748 In (1.90 Mm) ³	450 %	450 %	ISO 188
Tear Strength ^{4, 1} (0.0748 In (1.90 Mm))	120 lbf/in	21.0 kN/m	ASTM D624
Compression Set ⁵			ASTM D395B
75°f (24°c), 22 Hr	14 %	14 %	
212°f (100°c), 22 Hr	52 %	52 %	
Clash-Berg Modulus (-15°f (-26°c))	10000 psi	68.9 MPa	ASTM D1043

Technical Data Sheet

Alcryn Alcryn 2250 BK

Melt Processable Rubber

LyondellBasell Industries


Engineering Plastics

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness			ASTM D2240
Shore A, 0.0748 In (1.90 Mm), Compression Molded	46	46	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Brittleness Temperature	-132 °F	-91.0 °C	ASTM D746 ISO 812
Aging	Nominal Value (English)	Nominal Value (SI)	Test Method
Change in Durometer Hardness in Air ²			ASTM D573 ISO 188
Shore A, 257°f (125°c), 168 Hr	-2.0	-2.0	
Change in Volume ²			ASTM D471 ISO 1817
81°f (27°c), 168 Hr, In Reference Fuel B	24 %	24 %	
212°f (100°c), 168 Hr, In Astm #1 Oil	-39 %	-39 %	
212°f (100°c), 168 Hr, In Irm 903 Oil	32 %	32 %	
212°f (100°c), 168 Hr, In Water	7.0 %	7.0 %	
Fill Analysis	Nominal Value (English)	Nominal Value (SI)	Test Method
Melt Viscosity (374°f (190°c), 300 Sec ⁻¹)	160 Pa·s	160 Pa·s	ASTM D3835

Technical Data Sheet

Alcryn Alcryn 2250 BK

Melt Processable Rubber
 LyondellBasell Industries
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Processing (Melt) Temp	350 °F	177 °C

Notes

- ¹ Compression Molded
- ² 1.9 mm, Compression Molded
- ³ 7 days, Compression Molded
- ⁴ Die C
- ⁵ Type I pellets, 12.7 mm diameter, plied up from 1.9 mm slabs

Notes

These are typical property values not to be construed as specification limits.