

Technical Data Sheet

Accucomp NY0700L

Polyamide 6
LyondellBasell Industries
Engineering Plastics

General

Forms • Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.13	1.13 g/cm ³	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	261000 psi	1800 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	10200 psi	70.0 MPa	
Break	7540 psi	52.0 MPa	
Tensile Elongation			ASTM D638
Yield	6.0 %	6.0 %	
Break	260 %	260 %	
Flexural Modulus	392000 psi	2700 MPa	ASTM D790
Flexural Strength	15500 psi	107 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	1.0 ft·lb/in	55 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	120	120	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	140 °F	60.0 °C	
Melting Temperature	455 °F	235 °C	

Notes

These are typical property values not to be construed as specification limits.