



Technical Data Sheet

Fiberfil NY-6/15

Polyamide 6
LyondellBasell Industries
Engineering Plastics

General

- | | |
|------------------------|-------------------------------------|
| Filler / Reinforcement | • Glass Fiber, 15% Filler by Weight |
| Forms | • Pellets |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Density / Specific Gravity	1.24	1.24 g/cm ³	ASTM D792
----------------------------	------	------------------------	-----------

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Tensile Strength (73°F (23°C))	16000 psi	110 MPa	ASTM D638
--------------------------------	-----------	---------	-----------

Flexural Modulus - Secant (73°F (23°C))	711000 psi	4900 MPa	ASTM D790
---	------------	----------	-----------

Flexural Strength (73°F (23°C))	24800 psi	171 MPa	ASTM D790
---------------------------------	-----------	---------	-----------

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
--------	-------------------------	--------------------	-------------

Notched Izod Impact			ASTM D256
---------------------	--	--	-----------

73°F (23°C), 0.125 In (3.18 Mm)	1.1 ft·lb/in	60 J/m	
---------------------------------	--------------	--------	--

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
---------	-------------------------	--------------------	-------------

Deflection Temperature Under Load			ASTM D648
-----------------------------------	--	--	-----------

264 Psi (1.8 Mpa), Unannealed	392 °F	200 °C	
-------------------------------	--------	--------	--

Notes

These are typical property values not to be construed as specification limits.