



Technical Data Sheet

Matrixx FP62E33

Polyamide 6
 LyondellBasell Industries
 Engineering Plastics

General

Filler / Reinforcement	• Glass Fiber, 33% Filler by Weight
Uses	• Industrial Applications
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Density / Specific Gravity	1.38	1.38 g/cm ³	ASTM D792
----------------------------	------	------------------------	-----------

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Tensile Strength (Yield)	22000 psi	152 MPa	ASTM D638
--------------------------	-----------	---------	-----------

Flexural Modulus	1.20E+6 psi	8270 MPa	ASTM D790
------------------	-------------	----------	-----------

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
--------	-------------------------	--------------------	-------------

Notched Izod Impact	1.5 ft·lb/in	80 J/m	ASTM D256
---------------------	--------------	--------	-----------

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
---------	-------------------------	--------------------	-------------

Deflection Temperature Under Load			ASTM D648
-----------------------------------	--	--	-----------

66 Psi (0.45 Mpa), Unannealed	410 °F	210 °C	
-------------------------------	--------	--------	--

264 Psi (1.8 Mpa), Unannealed	390 °F	199 °C	
-------------------------------	--------	--------	--

Additional Information

1F932A/PR2871
 Revision: 5/2/2020

Technical Data Sheet

Matrixx FP62E33

Polyamide 6
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	160 to 200 °F	71 to 93 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Suggested Max Moisture	0.10 %	0.10 %
Rear Temperature	480 to 540 °F	249 to 282 °C
Middle Temperature	500 to 540 °F	260 to 282 °C
Front Temperature	500 to 540 °F	260 to 282 °C
Processing (Melt) Temp	480 to 540 °F	249 to 282 °C
Mold Temperature	180 to 200 °F	82 to 93 °C
Injection Rate	Fast	Fast
Back Pressure	< 50.0 psi	< 0.345 MPa
Cushion	0.250 to 0.500 in	6.35 to 12.7 mm

Injection Notes
 Dessicant dryer with -20°F dewpoint
 Screw Speed: Slow to Medium

Notes

These are typical property values not to be construed as specification limits.