

Technical Data Sheet

Matrixx FP63E13

Polyamide 6
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	160 to 200 °F	71 to 93 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Suggested Max Moisture	0.10 %	0.10 %
Rear Temperature	500 to 550 °F	260 to 288 °C
Middle Temperature	500 to 550 °F	260 to 288 °C
Front Temperature	500 to 550 °F	260 to 288 °C
Processing (Melt) Temp	500 to 560 °F	260 to 293 °C
Mold Temperature	180 to 200 °F	82 to 93 °C
Injection Rate	Fast	Fast
Back Pressure	< 50.0 psi	< 0.345 MPa
Cushion	0.250 to 0.500 in	6.35 to 12.7 mm

Injection Notes

- Screw Speed: Slow to Medium
- Dessicant dryer with -20°F dewpoint

Notes

These are typical property values not to be construed as specification limits.