

Technical Data Sheet

Matrixx WP63E20

Polyamide 6
LyondellBasell Industries
Engineering Plastics

General

- | | |
|------------------------|---------------------------------|
| Filler / Reinforcement | • Mineral, 20% Filler by Weight |
| Forms | • Pellets |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.29	1.29 g/cm ³	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	13300 psi	91.7 MPa	ASTM D638
Flexural Modulus - Tangent	670000 psi	4620 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	1.0 ft·lb/in	53 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
RTI Str	150 °F	65.6 °C	UL 746B
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.5 Mm))	HB	HB	UL 94

Notes

These are typical property values not to be construed as specification limits.