

Technical Data Sheet

# Schulamid 6 GB 15 U

Polyamide 6  
LyondellBasell Industries  
Engineering Plastics

**Product Description**

15% glass bead reinforced Polyamide 6 compound, UV-stabilized

**General**

Filler / Reinforcement	• Glass Bead, 15% Filler by Weight
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA6-GB

**Physical**

	Dry	Conditioned	Unit	Test Method
Density	1.23	--	g/cm <sup>3</sup>	ISO 1183/A
Viscosity Number	145	--	cm <sup>3</sup> /g	ISO 307

**Mechanical**

	Dry	Conditioned	Unit	Test Method
Tensile Modulus	493000 (3400)	138000 (950)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Break)	10400 (72.0)	6090 (42.0)	psi (MPa)	ISO 527-2/1A/5
Tensile Strain (Break)	9.0	> 50	%	ISO 527-2/1A/5

**Impact**

	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°f (-30°c)	1.7 (3.5)	--	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
73°f (23°c)	2.4 (5.0)	7.6 (16)	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°f (-30°c)	12 (26)	--	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
73°f (23°c)	21 ft·lb/in <sup>2</sup> (45 kJ/m <sup>2</sup> )	No Break	(kJ/m <sup>2</sup> )	

**Thermal**

	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
66 Psi (0.45 Mpa), Unannealed	329 (165)	--	°F (°C)	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	140 (60.0)	--	°F (°C)	ISO 75-2/Af
Vicat Softening Temperature				
--	378 (192)	--	°F (°C)	ISO 306/B50
--	410 (210)	--	°F (°C)	ISO 306/A50

**Flammability**

	Dry	Conditioned	Unit	Test Method
Burning Rate				
0.0787 In (2.00 Mm)	2.4 (60)	--	in/min (mm/min)	ISO 3795
0.0787 In (2.00 Mm)	2.4 (60)	--	in/min (mm/min)	FMVSS 302

Technical Data Sheet

# Schulamid 6 GB 15 U

Polyamide 6  
LyondellBasell Industries  
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	482 to 536 °F	250 to 280 °C
Mold Temperature	140 to 212 °F	60 to 100 °C

**Notes**

These are typical property values not to be construed as specification limits.