

Technical Data Sheet

# Schulamid 6 GBF 3015 FR 4

Polyamide 6  
LyondellBasell Industries  
Engineering Plastics

**Product Description**

30% glass fiber and glass beads reinforced flame-retardant Polyamide 6 grade with low warpage, high mechanical stability and high dimensional stability; without PBDE

**General**

Filler / Reinforcement	• Glass Bead\Glass Fiber, 30% Filler by Weight
Features	• Flame Retardant • Low Warpage
UL File Number	• E86615
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA6 (GF+GB)30 FR(17)

Physical	Dry	Conditioned	Unit	Test Method
----------	-----	-------------	------	-------------

Density	1.60	--	g/cm <sup>3</sup>	ISO 1183/A
Viscosity Number	145	--	cm <sup>3</sup> /g	ISO 307

Mechanical	Dry	Conditioned	Unit	Test Method
------------	-----	-------------	------	-------------

Tensile Modulus	1.28E+6 (8800)	725000 (5000)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Break)	18900 (130)	11600 (80.0)	psi (MPa)	ISO 527-2/1A/5
Tensile Strain (Break)	2.5	6.0	%	ISO 527-2/1A/5

Impact	Dry	Conditioned	Unit	Test Method
--------	-----	-------------	------	-------------

Charpy Notched Impact Strength				ISO 179/1eA
-22°f (-30°c)	1.9 (4.0)	--	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
73°f (23°c)	2.9 (6.0)	3.3 (7.0)	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°f (-30°c)	19 (40)	--	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
73°f (23°c)	24 (50)	25 (53)	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	

Thermal	Dry	Conditioned	Unit	Test Method
---------	-----	-------------	------	-------------

Deflection Temperature Under Load				
66 Psi (0.45 Mpa), Unannealed	410 (210)	--	°F (°C)	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	374 (190)	--	°F (°C)	ISO 75-2/Af
Vicat Softening Temperature				
--	401 (205)	--	°F (°C)	ISO 306/B50
--	410 (210)	--	°F (°C)	ISO 306/A50
Ball Pressure Test (392°f (200°c))	Pass	--		IEC 60695-10-2

Technical Data Sheet

# Schulamid 6 GBF 3015 FR 4

Polyamide 6  
LyondellBasell Industries  
Engineering Plastics

Thermal	Dry	Conditioned	Unit	Test Method
<b>RTI Elec</b>				
0.04 In (1.0 Mm)	149 (65.0)	--	°F (°C)	UL 746B
0.06 In (1.5 Mm)	149 (65.0)	--	°F (°C)	
0.12 In (3.0 Mm)	149 (65.0)	--	°F (°C)	
<b>RTI Imp</b>				
0.04 In (1.0 Mm)	149 (65.0)	--	°F (°C)	UL 746B
0.06 In (1.5 Mm)	149 (65.0)	--	°F (°C)	
0.12 In (3.0 Mm)	149 (65.0)	--	°F (°C)	
<b>RTI Str</b>				
0.04 In (1.0 Mm)	149 (65.0)	--	°F (°C)	UL 746B
0.06 In (1.5 Mm)	149 (65.0)	--	°F (°C)	
0.12 In (3.0 Mm)	149 (65.0)	--	°F (°C)	
<b>Electrical</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Comparative Tracking Index	200	--	V	IEC 60112
<b>Flammability</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
<b>Burning Rate</b>				
0.0394 In (1.00 Mm), Self-extinguishing	0.0	--	in/min (mm/min)	ISO 3795
0.0591 In (1.50 Mm), Self-extinguishing	0.0	--	in/min (mm/min)	
0.118 In (3.00 Mm), Self-extinguishing	0.0	--	in/min (mm/min)	
<b>Flame Rating</b>				
0.04 In (1.0 Mm)	V-0	--		UL 94 IEC 60695-11-10, -20
0.06 In (1.5 Mm)	• V-0 • 5VA	--		
0.12 In (3.0 Mm)	• V-0 • 5VA	--		
<b>Glow Wire Flammability Index</b>				
0.04 In (1.0 Mm)	1760 (960)	--	°F (°C)	IEC 60695-2-12
0.06 In (1.5 Mm)	1760 (960)	--	°F (°C)	
0.12 In (3.0 Mm)	1760 (960)	--	°F (°C)	
<b>Glow Wire Ignition Temperature</b>				
0.04 In (1.0 Mm)	1470 (800)	--	°F (°C)	IEC 60695-2-13
0.06 In (1.5 Mm)	1470 (800)	--	°F (°C)	
0.12 In (3.0 Mm)	1470 (800)	--	°F (°C)	



Technical Data Sheet

**Schulamid 6 GBF 3015 FR 4**


Polyamide 6  
LyondellBasell Industries  
Engineering Plastics

Flammability	Dry	Conditioned	Unit	Test Method
Oxygen Index	35	--	%	ISO 4589-2

Technical Data Sheet

**Schulamid 6 GBF 3015 FR 4**

Polyamide 6  
LyondellBasell Industries  
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	464 to 500 °F	240 to 260 °C
Mold Temperature	140 to 194 °F	60 to 90 °C
Back Pressure	< 591 in/min	< 15 m/min
Screw Speed	< 591 in/min	< 15 m/min

**Injection Notes**  
Mould surface contacting melt should be of non-corrosive steel (content of chrome > 12%)

**Notes**  
These are typical property values not to be construed as specification limits.