

Technical Data Sheet

# Schulamid 6 GF 30 FR 2 BLACK

Polyamide 6  
LyondellBasell Industries  
Engineering Plastics

**Product Description**  
30% glass fibre reinforced flame-retardant Polyamide 6 grade; halogen free, heat stabilized.

| General                |                                     |
|------------------------|-------------------------------------|
| Filler / Reinforcement | • Glass Fiber, 30% Filler by Weight |
| Features               | • Flame Retardant • Halogen Free    |
| UL File Number         | • E86615                            |
| Processing Method      | • Injection Molding                 |
| Resin ID (ISO 1043)    | • PA6 GF30 FR(40)                   |

| Physical                           | Dry                | Conditioned      | Unit  | Test Method    |
|------------------------------------|--------------------|------------------|---|----------------|
| Density                            | 1.43               | --               | g/cm <sup>3</sup>                             | ISO 1183/A     |
| Viscosity Number                   | 145                | --               | cm <sup>3</sup> /g                            | ISO 307        |
| Mechanical                         | Dry                | Conditioned      | Unit  | Test Method    |
| Tensile Modulus                    | 1.74E+6<br>(12000) | 943000<br>(6500) | psi<br>(MPa)                                  | ISO 527-1/1A/1 |
| Tensile Stress (Break)             | 20300<br>(140)     | 13800<br>(95.0)  | psi<br>(MPa)                                  | ISO 527-2/1A/5 |
| Tensile Strain (Break)             | 3.0                | 6.0              | %   | ISO 527-2/1A/5 |
| Impact                             | Dry                | Conditioned      | Unit  | Test Method    |
| Charpy Notched Impact Strength     |                    |                  |   | ISO 179/1eA    |
| -22°F (-30°C)                      | 4.3<br>(9.0)       | --               | ft·lb/in <sup>2</sup><br>(kJ/m <sup>2</sup> ) |                |
| 73°F (23°C)                        | 5.7<br>(12)        | 7.6<br>(16)      | ft·lb/in <sup>2</sup><br>(kJ/m <sup>2</sup> ) |                |
| Charpy Unnotched Impact Strength   |                    |                  |   | ISO 179/1eU    |
| -22°F (-30°C)                      | 29<br>(60)         | --               | ft·lb/in <sup>2</sup><br>(kJ/m <sup>2</sup> ) |                |
| 73°F (23°C)                        | 33<br>(70)         | 33<br>(70)       | ft·lb/in <sup>2</sup><br>(kJ/m <sup>2</sup> ) |                |
| Thermal                            | Dry                | Conditioned      | Unit  | Test Method    |
| Deflection Temperature Under Load  |                    |                  |   |                |
| 66 Psi (0.45 Mpa), Unannealed      | 419<br>(215)       | --               | °F<br>(°C)                                    | ISO 75-2/Bf    |
| 264 Psi (1.8 Mpa), Unannealed      | 399<br>(204)       | --               | °F<br>(°C)                                    | ISO 75-2/Af    |
| Vicat Softening Temperature        |                    |                  |   |                |
| --                                 | 397<br>(203)       | --               | °F<br>(°C)                                    | ISO 306/B50    |
| --                                 | 414<br>(212)       | --               | °F<br>(°C)                                    | ISO 306/A50    |
| Ball Pressure Test (392°F (200°C)) | Pass               | --               |   | IEC 60695-10-2 |

Technical Data Sheet

# Schulamid 6 GF 30 FR 2 BLACK

Polyamide 6  
LyondellBasell Industries  
Engineering Plastics

| Electrical                               | Dry           | Conditioned | Unit               | Test Method             |
|--|---------------|-------------|--------------------|-------------------------|
| Surface Resistivity                      | > 1.0E+15     | > 1.0E+12   | ohms               | IEC 60093               |
| Volume Resistivity                       | > 1.0E+13     | > 1.0E+10   | ohms·m             | IEC 62631-3-1           |
| Electric Strength <sup>1</sup>           |               |             |                    | IEC 60243-1             |
| 73°F (23°C), 0.0394 In (1.00 Mm), In Oil | 710<br>(28)   | --          | V/mil<br>(kV/mm)   |                         |
| Comparative Tracking Index               | 475           | --          | V                  | IEC 60112               |
| Flammability                             | Dry           | Conditioned | Unit               | Test Method             |
| Burning Rate                             |               |             |                    | ISO 3795                |
| 0.0295 In (0.750 Mm), Self-extinguishing | 0.0           | --          | in/min<br>(mm/min) |                         |
| 0.0591 In (1.50 Mm), Self-extinguishing  | 0.0           | --          | in/min<br>(mm/min) |                         |
| 0.118 In (3.00 Mm), Self-extinguishing   | 0.0           | --          | in/min<br>(mm/min) |                         |
| Flammability Classification              |               |             |                    | IEC 60695-11-10,<br>-20 |
| 0.030 In (0.75 Mm)                       | V-0           | --          |                    |                         |
| 0.06 In (1.5 Mm)                         | V-0           | --          |                    |                         |
| 0.12 In (3.0 Mm)                         | V-0           | --          |                    |                         |
| Glow Wire Flammability Index             |               |             |                    | IEC 60695-2-12          |
| 0.030 In (0.75 Mm)                       | 1760<br>(960) | --          | °F<br>(°C)         |                         |
| 0.06 In (1.5 Mm)                         | 1760<br>(960) | --          | °F<br>(°C)         |                         |
| 0.12 In (3.0 Mm)                         | 1760<br>(960) | --          | °F<br>(°C)         |                         |
| Glow Wire Ignition Temperature           |               |             |                    | IEC 60695-2-13          |
| 0.030 In (0.75 Mm)                       | 1380<br>(750) | --          | °F<br>(°C)         |                         |
| 0.06 In (1.5 Mm)                         | 1380<br>(750) | --          | °F<br>(°C)         |                         |
| 0.12 In (3.0 Mm)                         | 1380<br>(750) | --          | °F<br>(°C)         |                         |
| Oxygen Index                             | 32            | --          | %                  | ISO 4589-2              |

Technical Data Sheet

# Schulamid 6 GF 30 FR 2 BLACK

Polyamide 6  
LyondellBasell Industries  
Engineering Plastics



| Injection              | Dry (English)   | Dry (SI)         |
|------------------------|-----------------|------------------|
| Drying Temperature     | 176 °F          | 80 °C            |
| Drying Time            | 3.0 to 4.0 hr   | 3.0 to 4.0 hr    |
| Suggested Max Moisture | 0.04 to 0.10 %  | 0.04 to 0.10 %   |
| Processing (Melt) Temp | 464 to 500 °F   | 240 to 260 °C    |
| Mold Temperature       | 140 to 212 °F   | 60 to 100 °C     |
| Injection Rate         | Slow-Moderate   | Slow-Moderate    |
| Back Pressure          | 290 to 1160 psi | 2.00 to 8.00 MPa |
| Screw Speed            | < 591 in/min    | < 15 m/min       |

**Notes**

<sup>1</sup> 2000 V/sec

**Notes**

These are typical property values not to be construed as specification limits.