

Technical Data Sheet

Schulamid 6 GF 35

Polyamide 6
LyondellBasell Industries
Engineering Plastics

Product Description

35% glass fiber reinforced Polyamide 6

General

Filler / Reinforcement	• Glass Fiber, 35% Filler by Weight
Features	• Good Flow • High Stiffness • High Strength • Oil Resistant
UL File Number	• E86615
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA6-GF35

Physical	Dry	Conditioned	Unit	Test Method
----------	-----	-------------	------	-------------

Density	1.41	--	g/cm ³	ISO 1183/A
Viscosity Number	145	--	cm ³ /g	ISO 307

Mechanical	Dry	Conditioned	Unit	Test Method
------------	-----	-------------	------	-------------

Tensile Modulus	1.60E+6 (11000)	1.02E+6 (7000)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Break)	26100 (180)	16000 (110)	psi (MPa)	ISO 527-2/1A/5
Tensile Strain (Break)	3.4	6.0	%	ISO 527-2/1A/5

Impact	Dry	Conditioned	Unit	Test Method
--------	-----	-------------	------	-------------

Charpy Notched Impact Strength				ISO 179/1eA
-22°F (-30°C)	4.8 (10)	--	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	7.1 (15)	15 (32)	ft·lb/in ² (kJ/m ²)	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F (-30°C)	33 (70)	--	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	43 ft·lb/in ² (90 kJ/m ²)	No Break	(kJ/m ²)	

Hardness	Dry	Conditioned	Unit	Test Method
----------	-----	-------------	------	-------------

Ball Indentation Hardness (H 358/30)	33400 (230)	--	psi (MPa)	ISO 2039-1
--------------------------------------	----------------	----	--------------	------------

Thermal	Dry	Conditioned	Unit	Test Method
---------	-----	-------------	------	-------------

Deflection Temperature Under Load				
66 Psi (0.45 Mpa), Unannealed	428 (220)	--	°F (°C)	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	410 (210)	--	°F (°C)	ISO 75-2/Af
Vicat Softening Temperature	410 (210)	--	°F (°C)	ISO 306/B50
Ball Pressure Test (302°F (150°C))	Pass	--		IEC 60695-10-2

Technical Data Sheet

Schulamid 6 GF 35

Polyamide 6
LyondellBasell Industries
Engineering Plastics

Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	> 1.0E+15	> 1.0E+12	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	> 1.0E+10	ohms·m	IEC 62631-3-1
Comparative Tracking Index	450	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate				
0.0787 In (2.00 Mm)	1.2 (30)	--	in/min (mm/min)	ISO 3795
0.0787 In (2.00 Mm)	1.2 (30)	--	in/min (mm/min)	FMVSS 302
Flammability Classification				IEC 60695-11-10, -20
0.06 In (1.5 Mm)	HB	--		
0.12 In (3.0 Mm)	HB	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.06 In (1.5 Mm)	--	1200 (650)	°F (°C)	
0.12 In (3.0 Mm)	--	1200 (650)	°F (°C)	

Technical Data Sheet

Schulamid 6 GF 35

Polyamide 6
LyondellBasell Industries
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	482 to 536 °F	250 to 280 °C
Mold Temperature	140 to 212 °F	60 to 100 °C

Notes

These are typical property values not to be construed as specification limits.