

Technical Data Sheet

Schulamid 6 GF 7 FR 4 K1681

Polyamide 6
LyondellBasell Industries
Engineering Plastics

Product Description

7% glass fibre reinforced flame retardant PA-6 grade; incandescent wire test without flame; without PBDE; GWIT > 800°C

General

Filler / Reinforcement	• Glass Fiber, 7.0% Filler by Weight
Features	• Flame Retardant
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA6 GF7 FR(17+30)

Physical	Dry	Conditioned	Unit	Test Method
Density	1.32	--	g/cm ³	ISO 1183/A
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	725000 (5000)	334000 (2300)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Break)	10900 (75.0)	5800 (40.0)	psi (MPa)	ISO 527-2/1A/5
Tensile Strain (Break)	3.4	19	%	ISO 527-2/1A/5
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F (-30°C)	1.7 (3.5)	--	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	1.7 (3.5)	4.2 (8.8)	ft·lb/in ² (kJ/m ²)	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F (-30°C)	14 (30)	--	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	17 (35)	37 (78)	ft·lb/in ² (kJ/m ²)	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
66 Psi (0.45 Mpa), Unannealed	406 (208)	--	°F (°C)	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	338 (170)	--	°F (°C)	ISO 75-2/Af
Vicat Softening Temperature				
--	401 (205)	--	°F (°C)	ISO 306/B50
--	424 (218)	--	°F (°C)	ISO 306/A120
Ball Pressure Test (392°F (200°C))	Pass	--		IEC 60695-10-2

Technical Data Sheet

Schulamid 6 GF 7 FR 4 K1681

Polyamide 6
LyondellBasell Industries
Engineering Plastics

Thermal	Dry	Conditioned	Unit	Test Method
RTI Elec				UL 746B
0.015 In (0.38 Mm)	266 (130)	--	°F (°C)	
0.030 In (0.75 Mm)	266 (130)	--	°F (°C)	
0.06 In (1.5 Mm)	266 (130)	--	°F (°C)	
0.12 In (3.0 Mm)	266 (130)	--	°F (°C)	
RTI Imp				UL 746B
0.015 In (0.38 Mm)	167 (75.0)	--	°F (°C)	
0.030 In (0.75 Mm)	194 (90.0)	--	°F (°C)	
0.06 In (1.5 Mm)	212 (100)	--	°F (°C)	
0.12 In (3.0 Mm)	212 (100)	--	°F (°C)	
RTI Str				UL 746B
0.015 In (0.38 Mm)	212 (100)	--	°F (°C)	
0.030 In (0.75 Mm)	230 (110)	--	°F (°C)	
0.06 In (1.5 Mm)	248 (120)	--	°F (°C)	
0.12 In (3.0 Mm)	248 (120)	--	°F (°C)	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	> 1.0E+15	--	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	--	ohms·m	IEC 62631-3-1
Comparative Tracking Index	275	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746A
0.015 In (0.38 Mm)	PLC 0	--		
0.030 In (0.75 Mm)	PLC 0	--		
0.06 In (1.5 Mm)	PLC 0	--		
0.12 In (3.0 Mm)	PLC 0	--		
Hot-wire Ignition (HWI)				UL 746A
0.015 In (0.38 Mm)	PLC 3	--		
0.030 In (0.75 Mm)	PLC 0	--		
0.06 In (1.5 Mm)	PLC 0	--		
0.12 In (3.0 Mm)	PLC 0	--		



Technical Data Sheet

Schulamid 6 GF 7 FR 4 K1681


Polyamide 6
LyondellBasell Industries
Engineering Plastics

Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification				IEC 60695-11-10, -20
0.015 In (0.38 Mm)	V-2	--		
0.06 In (1.5 Mm)	V-2	--		
0.12 In (3.0 Mm)	V-2	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.015 In (0.38 Mm)	1560 (850)	--	°F (°C)	
0.030 In (0.75 Mm)	1560 (850)	--	°F (°C)	
0.06 In (1.5 Mm)	1760 (960)	--	°F (°C)	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.015 In (0.38 Mm)	1520 (825)	--	°F (°C)	
0.030 In (0.75 Mm)	1520 (825)	--	°F (°C)	
0.06 In (1.5 Mm)	1560 (850)	--	°F (°C)	
Oxygen Index	23	--	%	ISO 4589-2

Technical Data Sheet

Schulamid 6 GF 7 FR 4 K1681

Polyamide 6
LyondellBasell Industries
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Suggested Max Moisture	0.10 %	0.10 %
Processing (Melt) Temp	464 to 500 °F	240 to 260 °C
Mold Temperature	140 to 194 °F	60 to 90 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	290 to 1160 psi	2.00 to 8.00 MPa
Screw Speed	< 591 in/min	< 15 m/min

Injection Notes

Mould surface contacting melt should be of non-corrosive steel (content of chrome > 12%)

Notes

These are typical property values not to be construed as specification limits.