

Technical Data Sheet

# SCHULAMID® 6 HV 0 H FR

Polyamide 6  
Engineering Plastics

**Product Description**

High viscosity flame-retardant and heat stabilized Polyamide 6 grade; halogen- and phosphorus-free

**General**

Features	<ul style="list-style-type: none"> <li>Flame Retardant</li> <li>Halogen Free</li> </ul>	<ul style="list-style-type: none"> <li>Heat Stabilized</li> <li>High Viscosity</li> </ul>	<ul style="list-style-type: none"> <li>Low (to None) Phosphorus Content</li> </ul>
UL File Number	<ul style="list-style-type: none"> <li>E86615</li> </ul>		
Processing Method	<ul style="list-style-type: none"> <li>Extrusion</li> </ul>	<ul style="list-style-type: none"> <li>Injection Molding</li> </ul>	
Resin ID (ISO 1043)	<ul style="list-style-type: none"> <li>PA6 FR(30)</li> </ul>		

Physical	Dry	Conditioned	Unit	Test Method
----------	-----	-------------	------	-------------

Density	1.20	--	g/cm <sup>3</sup>	ISO 1183/A
Viscosity Number	195	--	cm <sup>3</sup> /g	ISO 307

Mechanical	Dry	Conditioned	Unit	Test Method
------------	-----	-------------	------	-------------

Tensile Modulus	464000 (3200)	174000 (1200)	psi (MPa)	ISO 527-2/1A/1
Tensile Stress (Yield)	10900 (75.0)	7250 (50.0)	psi (MPa)	ISO 527-2/1A/50
Tensile Strain (Yield)	4.0	> 50	%	ISO 527-2/1A/50

Impact	Dry	Conditioned	Unit	Test Method
--------	-----	-------------	------	-------------

Charpy Notched Impact Strength				ISO 179/1eA
-22°F (-30°C)	1.9 (4.0)	--	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
73°F (23°C)	2.4 (5.0)	5.7 (12)	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F (-30°C)	No Break	--		
73°F (23°C)	No Break	No Break		

Thermal	Dry	Conditioned	Unit	Test Method
---------	-----	-------------	------	-------------

Heat Deflection Temperature				
66 psi (0.45 MPa), Unannealed	387 (197)	--	°F (°C)	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	154 (68.0)	--	°F (°C)	ISO 75-2/af
Vicat Softening Temperature				
--	421 (216)	--	°F (°C)	ISO 306/A50
--	392 (200)	--	°F (°C)	ISO 306/B50
Ball Pressure Test (392°F (200°C))	Pass	--		IEC 60695-10-2

Technical Data Sheet

# SCHULAMID® 6 HV 0 H FR

Polyamide 6  
Engineering Plastics

Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+15	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+13	1.0E+10	ohms·m	IEC 62631-3-1
Electric Strength	790 (31)	710 (28)	V/mil (kV/mm)	IEC 60243-1
Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate				ISO 3795
0.0295 in (0.750 mm), Self-Extinguishing	0.0	--	in/min (mm/min)	
0.0591 in (1.50 mm), Self-Extinguishing	0.0	--	in/min (mm/min)	
0.118 in (3.00 mm), Self-Extinguishing	0.0	--	in/min (mm/min)	
Flammability Classification				IEC 60695-11-10, -20
0.030 in (0.75 mm)	V-0	--		
0.06 in (1.5 mm)	V-0	--		
0.12 in (3.0 mm)	V-0	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.030 in (0.75 mm)	1760 (960)	--	°F (°C)	
0.06 in (1.5 mm)	1760 (960)	--	°F (°C)	
0.12 in (3.0 mm)	1760 (960)	--	°F (°C)	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.030 in (0.75 mm)	1340 (725)	--	°F (°C)	
0.06 in (1.5 mm)	1340 (725)	--	°F (°C)	
0.12 in (3.0 mm)	1340 (725)	--	°F (°C)	
Oxygen Index	34	--	%	ISO 4589-2

Technical Data Sheet

# SCHULAMID® 6 HV 0 H FR

Polyamide 6  
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Suggested Max Regrind	25 %	25 %
Processing (Melt) Temp	446 to 500 °F	230 to 260 °C
Mold Temperature	140 to 194 °F	60 to 90 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	290 to 1160 psi	2.00 to 8.00 MPa
Back Pressure	290 to 1160 psi	2.00 to 8.00 MPa
Screw Speed	591 in/min	15 m/min

**Injection Notes**

During transport one component of the dryblend can go more to the bottom. It is therefore recommended to tumble the material before use to assure an even distribution of the dryblend components.

**Notes**

These are typical property values not to be construed as specification limits.