

Technical Data Sheet

# Schulamid 6 LGF30 12mm

Polyamide 6  
LyondellBasell Industries  
Engineering Plastics

**Product Description**

30% long glass fiber reinforced Polyamide 6

**General**

Filler / Reinforcement	• Long Glass Fiber, 30% Filler by Weight
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA6-GF30

**Physical**

	Dry	Conditioned	Unit	Test Method
Density	1.37	--	g/cm <sup>3</sup>	ISO 1183/A
Viscosity Number	155	--	cm <sup>3</sup> /g	ISO 307

**Mechanical**

	Dry	Conditioned	Unit	Test Method
Tensile Modulus	1.48E+6 (10200)	928000 (6400)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Break)	29000 (200)	17400 (120)	psi (MPa)	ISO 527-2/1A/5
Tensile Strain (Break)	2.6	3.6	%	ISO 527-2/1A/5
Flexural Modulus	1.54E+6 (10600)	--	psi (MPa)	ISO 178
Flexural Stress	43500 (300)	--	psi (MPa)	ISO 178

**Impact**

	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°f (-30°c)	7.1 (15)	--	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
73°f (23°c)	9.0 (19)	12 (25)	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°f (-30°c)	26 (55)	--	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
73°f (23°c)	31 (65)	43 (90)	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	

**Thermal**

	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
66 Psi (0.45 Mpa), Unannealed	439 (226)	--	°F (°C)	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	419 (215)	--	°F (°C)	ISO 75-2/Af

**Electrical**

	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index	400	--	V	IEC 60112

Technical Data Sheet

**Schulamid 6 LGF30 12mm**

Polyamide 6  
LyondellBasell Industries  
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	482 to 536 °F	250 to 280 °C
Mold Temperature	140 to 212 °F	60 to 100 °C

**Notes**

These are typical property values not to be construed as specification limits.