

Technical Data Sheet

Schulamid 6 MV HI FC K2507 NAT



Polyamide 6

Product Description

Schulamid 6 MV HI FC K2507 NAT is a Polyamide 6 material and is typically used in Injection Molding applications. Features include: Grease Resistant, High Impact Resistance, Low Temperature Toughness, Medium Viscosity, and Oil Resistant.

Processing Method	Injection Molding
Attribute	Grease Resistant; High Impact Resistance; Low Temperature Toughness; Medium Viscosity; Oil Resistant
Resin ID	PA6-I

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density, (Method A)	1.11	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield			
(Type 1A, 50 mm/min)	60.0	MPa	ISO 527-2
(Type 1A, 50 mm/min) - Conditioned	35.0	MPa	ISO 527-2
Nominal Tensile Strain at Break			
(50 mm/min, Type 1A) - Conditioned	>100	%	ISO 527-2
(50 mm/min, Type 1A)	>50	%	ISO 527-2
Tensile Strain at Yield			
(Type 1A, 50 mm/min)	4.2	%	ISO 527-2
(Type 1A, 50 mm/min) - Conditioned	20	%	ISO 527-2
Tensile Modulus			
(1 mm/min, Type 1A)	2200	MPa	ISO 527-1
(1 mm/min, Type 1A) - Conditioned	800	MPa	ISO 527-1
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	16	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	10	kJ/m ²	ISO 179
(23 °C, Type 1, Edgewise, Notch A) - Conditioned	60	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	No Break		ISO 179
(-30 °C, Type 1, Edgewise)	No Break		ISO 179
(23 °C, Type 1, Edgewise) - Conditioned	No Break		ISO 179
Hardness			

Ball Indentation Hardness			
(H 358/30)	110	MPa	ISO 2039-1
(H 358/30) - Conditioned	60.0	MPa	ISO 2039-1
Thermal			
Vicat Softening Temperature			
(B (50N), 50 °C/h)	175	°C	ISO 306
(A (10N), 50 °C/h)	215	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	140	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	60.0	°C	ISO 75-2/A
RTI Elec			
(1.5 mm)	65.0	°C	UL 746B
(3.0 mm)	65.0	°C	UL 746B
RTI Imp			
(1.5 mm)	65.0	°C	UL 746B
(3.0 mm)	65.0	°C	UL 746B
RTI Str			
(1.5 mm)	65.0	°C	UL 746B
(3.0 mm)	65.0	°C	UL 746B
Electrical			
Volume Resistivity	>1.0E+13	ohm*m	IEC 62631-3-1
- Conditioned	>1.0E+10	ohm*m	IEC 62631-3-1
Comparative Tracking Index (CTI)	600	V	IEC 60112
Surface Resistivity	>1.0E+15	ohm	IEC 60093
- Conditioned	>1.0E+12	ohm	IEC 60093
Flammable			
Burning Rate			
(2.00 mm)	<100	mm/min	ISO 3795
(2.00 mm)	<100	mm/min	FMVSS 302
Glow Wire Flammability Index			
(1.5 mm)	650	°C	IEC 60695-2-12
(3.0 mm)	650	°C	IEC 60695-2-12
Additional Information			
Water Absorption 23C/50RH	2.3	%	ISO 62
UL Information			
Flammability Classification			
(0.75 mm)	HB		IEC 60695-11-10, -20
(1.5 mm)	HB		IEC 60695-11-10, -20
(3.0 mm)	HB		IEC 60695-11-10, -20
UL File Number	E86615		
Injection Parameters			
	Nominal Value	Units	
Drying Time	3.0 to 4.0	hr	
Drying Temperature	80	°C	
Suggested Max Moisture	0.040 to 0.10	%	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	60 to 90	°C	