

Technical Data Sheet

SCHULAMID® 6 GF 15 FR 4 K1681 DEEP BLACK 96.8086

Polyamide 6
Engineering Plastics

Product Description
15% glass fibre reinforced flame-retardant Polyamide 6 grade without PBDE

General	
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
UL File Number	• E86615
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA6 GF15 FR(17+30)

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.38 g/cm ³	1.38 g/cm ³	ISO 1183/A
Viscosity Number	136 cm ³ /g	136 cm ³ /g	ISO 307

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	1.04E+6 psi	7200 MPa	ISO 527-2/1A/1
Tensile Stress (Break, 73°F (23°C))	17800 psi	123 MPa	ISO 527-2/1A/5
Tensile Strain (Break, 73°F (23°C))	3.0 %	3.0 %	ISO 527-2/1A/5

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	3.0 ft·lb/in ²	6.2 kJ/m ²	
73°F (23°C)	3.1 ft·lb/in ²	6.6 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	21 ft·lb/in ²	44 kJ/m ²	
73°F (23°C)	25 ft·lb/in ²	52 kJ/m ²	

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature			
66 psi (0.45 MPa), Unannealed	415 °F	213 °C	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	387 °F	197 °C	ISO 75-2/af
Vicat Softening Temperature			
--	415 °F	213 °C	ISO 306/A50
--	401 °F	205 °C	ISO 306/B50

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Comparative Tracking Index ¹	225 V	225 V	IEC 60112

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating			
0.016 in (0.40 mm)	V-2	V-2	UL 94 IEC 60695-11-10,-20
0.031 in (0.8 mm)	V-2	V-2	UL 94
0.06 in (1.6 mm)	V-2	V-2	UL 94 IEC 60695-11-10,-20
0.13 in (3.2 mm)	V-2	V-2	UL 94 IEC 60695-11-10,-20
0.03 in (0.8 mm)	V-2	V-2	IEC 60695-11-10,-20

SCHULAMID[®] 6 GF 15 FR 4 K1681 DEEP BLACK 96.8086

Polyamide 6
Engineering Plastics

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Glow Wire Flammability Index			IEC 60695-2-12
0.015 in (0.38 mm)	1470 °F	800 °C	
0.030 in (0.75 mm)	1760 °F	960 °C	
0.06 in (1.5 mm)	1760 °F	960 °C	
0.12 in (3.0 mm)	1760 °F	960 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.015 in (0.38 mm)	1520 °F	825 °C	
0.030 in (0.75 mm)	1650 °F	900 °C	
0.06 in (1.5 mm)	1650 °F	900 °C	
0.12 in (3.0 mm)	1650 °F	900 °C	
Oxygen Index	27 %	27 %	ISO 4589-2

Technical Data Sheet

SCHULAMID® 6 GF 15 FR 4 K1681 DEEP BLACK 96.8086

Polyamide 6
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Suggested Max Regrind	25 %	25 %
Processing (Melt) Temp	464 to 518 °F	240 to 270 °C
Mold Temperature	122 to 176 °F	50 to 80 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	290 to 1160 psi	2.00 to 8.00 MPa
Screw Speed	< 591 in/min	< 15 m/min

Injection Notes

Mould surface contacting melt should be of non-corrosive steel (content of chrome > 12%)