

Technical Data Sheet

**Schulamid 6 GB15 BLK968001**



Polyamide 6

**Product Description**

15% glass bead filled PA 6

**Processing Method** Injection Molding

**Filler/Reinforcement** Glass Bead, 15%

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Density, (Method A)	1.23	g/cm <sup>3</sup>	ISO 1183
Viscosity Number	145	cm <sup>3</sup> /g	ISO 307
<b>Mechanical</b>			
Tensile Strain at Break			
(Type 1A, 5 mm/min)	9.0	%	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	>50	%	ISO 527-2
Tensile Stress at Break			
(Type 1A, 5 mm/min)	72.0	MPa	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	42.0	MPa	ISO 527-2
Tensile Modulus			
(1 mm/min, Type 1A)	3400	MPa	ISO 527-1
(1 mm/min, Type 1A) - Conditioned	950	MPa	ISO 527-1
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	5.0	kJ/m <sup>2</sup>	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	3.5	kJ/m <sup>2</sup>	ISO 179
(23 °C, Type 1, Edgewise, Notch A) - Conditioned	16	kJ/m <sup>2</sup>	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	45	kJ/m <sup>2</sup>	ISO 179
(-30 °C, Type 1, Edgewise)	26	kJ/m <sup>2</sup>	ISO 179
(23 °C, Type 1, Edgewise) - Conditioned	No Break		ISO 179
<b>Thermal</b>			
Vicat Softening Temperature			
(B (50N), 50 °C/h)	192	°C	ISO 306
(A (10N), 120 °C/h)	210	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	165	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	60.0	°C	ISO 75-2/A
<b>Electrical</b>			

Volume Resistivity	>1.0E+13	ohm*m	IEC 62631-3-1
Comparative Tracking Index (CTI)	450	V	IEC 60112
Surface Resistivity	>1.0E+15	ohm	IEC 60093

**Flammable**

Burning Rate			
(2.00 mm)	40	mm/min	ISO 3795
(2.00 mm)	40	mm/min	FMVSS 302
Glow Wire Flammability Index	650	°C	IEC 60695-2-12

**UL Information**

Flammability Classification, (1.5 mm)	HB		IEC 60695-11-10, -20
---------------------------------------	----	--	----------------------

<b>Injection Parameters</b>	<b>Nominal Value</b>	<b>Units</b>
Drying Time	3.0 to 4.0	hr
Drying Temperature	80	°C
Suggested Max Moisture	0.040 to 0.10	%
Processing (Melt) Temp	250 to 280	°C
Mold Temperature	60 to 100	°C