

## Technical Data Sheet

**Schulamid 6 GB30 H LS GRY967844**

Polyamide 6

**Product Description**

30% glass bead filled PA 6

**Processing Method** Injection Molding**Filler/Reinforcement** Glass Bead, 30%

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Density, (Method A)	1.36	g/cm <sup>3</sup>	ISO 1183
Viscosity Number	145	cm <sup>3</sup> /g	ISO 307
<b>Mechanical</b>			
Tensile Strain at Break			
(Type 1A, 5 mm/min)	8.0	%	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	12	%	ISO 527-2
Tensile Stress at Break			
(Type 1A, 5 mm/min)	80.0	MPa	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	50.0	MPa	ISO 527-2
Tensile Modulus			
(1 mm/min, Type 1A)	4500	MPa	ISO 527-1
(1 mm/min, Type 1A) - Conditioned	1800	MPa	ISO 527-1
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	6.0	kJ/m <sup>2</sup>	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	4.0	kJ/m <sup>2</sup>	ISO 179
(23 °C, Type 1, Edgewise, Notch A) - Conditioned	14	kJ/m <sup>2</sup>	ISO 179
(-30 °C, Type 1, Edgewise, Notch A) - Conditioned	4.0	kJ/m <sup>2</sup>	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	30	kJ/m <sup>2</sup>	ISO 179
(-30 °C, Type 1, Edgewise)	28	kJ/m <sup>2</sup>	ISO 179
(23 °C, Type 1, Edgewise) - Conditioned	45	kJ/m <sup>2</sup>	ISO 179
(-30 °C, Type 1, Edgewise) - Conditioned	35	kJ/m <sup>2</sup>	ISO 179
<b>Hardness</b>			
Ball Indentation Hardness, (H 358/30)	165	MPa	ISO 2039-1
Ball Pressure Test, (105 °C)	Pass		IEC 60695-10-2
<b>Thermal</b>			

<b>Vicat Softening Temperature</b>			
(B (50N), 50 °C/h)	200	°C	ISO 306
(A (10N), 120 °C/h)	210	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	180	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	70.0	°C	ISO 75-2/A
<b>Electrical</b>			
Volume Resistivity	>1.0E+13	ohm*m	IEC 62631-3-1
Comparative Tracking Index (CTI)	450	V	IEC 60112
Surface Resistivity	>1.0E+15	ohm	IEC 60093
<b>Flammable</b>			
Burning Rate			
(2.00 mm)	80	mm/min	ISO 3795
(2.00 mm)	80	mm/min	FMVSS 302
Glow Wire Flammability Index	650	°C	IEC 60695-2-12
<b>UL Information</b>			
Flammability Classification, (1.5 mm)	HB		IEC 60695-11-10, -20

<b>Injection Parameters</b>	<b>Nominal Value</b>	<b>Units</b>
Drying Time	3.0 to 4.0	hr
Drying Temperature	80	°C
Suggested Max Moisture	0.040 to 0.10	%
Processing (Melt) Temp	250 to 280	°C
Mold Temperature	60 to 100	°C