

Technical Data Sheet

Schulamid 6 MT30 WD BLK968001

Polyamide 6

Product Description

30% talc filled Polyamide 6

Processing Method Injection Molding**Attribute** Good Surface Finish; Low Warpage; Medium Viscosity; Oil Resistant**Filler/Reinforcement** Talc, 30%**Resin ID** PA6-T30

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density, (Method A)	1.36	g/cm ³	ISO 1183
Viscosity Number	145	cm ³ /g	ISO 307
Mechanical			
Tensile Strain at Break			
(Type 1A, 5 mm/min)	3.0	%	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	15	%	ISO 527-2
Tensile Stress at Break			
(Type 1A, 5 mm/min)	73.0	MPa	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	45.0	MPa	ISO 527-2
Tensile Modulus			
(1 mm/min, Type 1A)	6500	MPa	ISO 527-1
(1 mm/min, Type 1A) - Conditioned	3300	MPa	ISO 527-1
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	4.0	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	3.0	kJ/m ²	ISO 179
(23 °C, Type 1, Edgewise, Notch A) - Conditioned	8.0	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	40	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise)	30	kJ/m ²	ISO 179
(23 °C, Type 1, Edgewise) - Conditioned	60	kJ/m ²	ISO 179
Thermal			
Vicat Softening Temperature			
(B (50N), 50 °C/h)	200	°C	ISO 306
(A (10N), 50 °C/h)	215	°C	ISO 306

Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	200 °C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	100 °C	ISO 75-2/A
Flammable		
Burning Rate		
(2.00 mm)	48 mm/min	ISO 3795
(2.00 mm)	48 mm/min	FMVSS 302

Injection Parameters	Nominal Value	Units
Drying Time	3.0 to 4.0	hr
Drying Temperature	80	°C
Suggested Max Moisture	0.040 to 0.10	%
Processing (Melt) Temp	250 to 280	°C
Mold Temperature	60 to 100	°C