

## Technical Data Sheet

### Schulamid 6 MV HI K2513 BLK968079



Polyamide 6

#### Product Description

Impact modified polyamide 6 compound

**Processing Method** Extrusion; Injection Molding

**Attribute** Impact Modified

**Resin ID** PA6-I

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Volume Flow Rate, (260 °C/2.16 kg)	15	cm <sup>3</sup> /10 min	ISO 1133
Density, (Method A)	1.12	g/cm <sup>3</sup>	ISO 1183
Viscosity Number	155	cm <sup>3</sup> /g	ISO 307
<b>Mechanical</b>			
Tensile Stress at Yield			
(Type 1A, 50 mm/min)	71.0	MPa	ISO 527-2
(Type 1A, 50 mm/min) - Conditioned	36.0	MPa	ISO 527-2
Flexural Modulus	2700	MPa	ISO 178
Tensile Strain at Yield			
(Type 1A, 50 mm/min)	5.0	%	ISO 527-2
(Type 1A, 50 mm/min) - Conditioned	24	%	ISO 527-2
Tensile Modulus			
(1 mm/min, Type 1A)	2500	MPa	ISO 527-1
(1 mm/min, Type 1A) - Conditioned	700	MPa	ISO 527-1
Flexural Stress	85	MPa	ISO 178
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	10	kJ/m <sup>2</sup>	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	7.0	kJ/m <sup>2</sup>	ISO 179
(23 °C, Type 1, Edgewise, Notch A) - Conditioned	120	kJ/m <sup>2</sup>	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	No Break		ISO 179
(-30 °C, Type 1, Edgewise)	56	kJ/m <sup>2</sup>	ISO 179
(23 °C, Type 1, Edgewise) - Conditioned	No Break		ISO 179
<b>Flammable</b>			
Burning Rate			
(2.00 mm)	<100	mm/min	ISO 3795
(2.00 mm)	<100	mm/min	FMVSS 302

---

**Additional Information**

---

Water Absorption 23C/50RH

2.8 %

ISO 62

---

**Injection Parameters**

**Nominal  
Value Units**

---

Drying Time

3.0 to 4.0 hr

---

Drying Temperature

80 °C

---

Suggested Max Moisture

0.040 to  
0.10 %

---

Processing (Melt) Temp

250 to 270 °C

---

Mold Temperature

60 to 90 °C

---