

Technical Data Sheet

Schulamid 6 MV14 FR4 K1681 YEW962093

Polyamide 6

Product Description

5% glass fibre reinforced flame retardant PA-6 grade; incandescent wire test without flame; without PBDE; GWIT > 800°C

Processing Method	Injection Molding
Additive	Flame Retardant
Filler/Reinforcement	Glass Fiber, 5.0%
Resin ID	PA6 GF5 FR(17+30)

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density, (Method A)	1.30	g/cm ³	ISO 1183
Mechanical			
Tensile Strain at Break			
(Type 1A, 5 mm/min)	5.0	%	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	40	%	ISO 527-2
Tensile Stress at Break			
(Type 1A, 5 mm/min)	61.0	MPa	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	35.0	MPa	ISO 527-2
Tensile Modulus			
(1 mm/min, Type 1A)	4200	MPa	ISO 527-1
(1 mm/min, Type 1A) - Conditioned	1800	MPa	ISO 527-1
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	4.2	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	3.5	kJ/m ²	ISO 179
(23 °C, Type 1, Edgewise, Notch A) - Conditioned	9.0	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	32	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise)	31	kJ/m ²	ISO 179
(23 °C, Type 1, Edgewise) - Conditioned	No Break		ISO 179
Hardness			
Ball Pressure Test, (200 °C)	Pass		IEC 60695-10-2
Thermal			
Vicat Softening Temperature			
(B (50N), 50 °C/h)	201	°C	ISO 306
(A (10N), 120 °C/h)	215	°C	ISO 306

Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	207 °C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	143 °C	ISO 75-2/A

Electrical

Volume Resistivity	>1.0E+13 ohm*m	IEC 62631-3-1
Comparative Tracking Index (CTI)	275 V	IEC 60112
Surface Resistivity	>1.0E+15 ohm	IEC 60093

Flammable

Glow Wire Flammability Index		
(0.75 mm)	850 °C	IEC 60695-2-12
(1.5 mm)	960 °C	IEC 60695-2-12
(0.38 mm)	850 °C	IEC 60695-2-12
Glow Wire Ignition Temperature		
(0.75 mm)	825 °C	IEC 60695-2-13
(1.5 mm)	850 °C	IEC 60695-2-13
(0.38 mm)	825 °C	IEC 60695-2-13
Oxygen Index	23 %	ISO 4589-2

UL Information

Flammability Classification		
(0.38 mm)	V-2	IEC 60695-11-10, -20
(1.5 mm)	V-2	IEC 60695-11-10, -20
(3.0 mm)	V-2	IEC 60695-11-10, -20

Injection Parameters	Nominal Value	Units
Drying Time	4.0 to 6.0	hr
Drying Temperature	80	°C
Suggested Max Moisture	0.1	%
Screw Speed	<250	mm/sec
Processing (Melt) Temp	240 to 260	°C
Injection Rate	Slow-Moderate	
Back Pressure	20 to 80	bar
Mold Temperature	60 to 90	°C