

Technical Data Sheet

Schulamid P64E0UVBKBLK



Polyamide 6

Product Description

Schulamid P64E0UVBKBLK is a Polyamide 6 material and is typically used in Injection Molding applications. Features include: Heat Stabilized, and Impact Modified.

Processing Method	Injection Molding
Attribute	Heat Stabilized; Impact Modified
Forms	Pellets

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density - Specific Gravity	1.11	g/cm ³	ASTM D792
Mechanical			
Tensile Strength at Yield	60	MPa	ASTM D638
Flexural Modulus	2310	MPa	ASTM D790
Impact			
Notched Izod Impact	180	J/m	ASTM D256
Thermal			
Deflection Temperature Under Load Unannealed (264 psi)	52.2	°C	ASTM D648
Deflection Temperature Under Load Unannealed (66 psi)	141	°C	ASTM D648

Injection Parameters	Value	Units
Drying Time	4.0 to 6.0	hr
Drying Temperature	71 to 93	°C
Suggested Max Moisture	0.1	%
Processing (Melt) Temp	249 to 282	°C
Front Temperature	249 to 282	°C
Middle Temperature	249 to 282	°C
Rear Temperature	249 to 271	°C
Injection Rate	Fast	
Back Pressure	<0.345	MPa
Mold Temperature	66 to 93	°C
Cushion	6.35 to 12.7	mm