

## Technical Data Sheet

**Vitamide BT36 BLK B 201B 2-0698**

Polyamide 6

**Product Description**

*Vitamide* BT36 BLACK B 201B 2-0698 is a Polyamide 6 Glass Fiber, 30% filled material. Features include: Impact Modified.

<b>Attribute</b>	Impact Modified
<b>Additive</b>	Impact Modifier
<b>Application</b>	Lawn & Garden Equipment
<b>Filler/Reinforcement</b>	Glass Fiber, 30%

<b>Typical Properties</b>	<b>Nominal Value</b>	<b>Units</b>	<b>Test Method</b>
<b>Physical</b>			
Density	1.36	g/cm <sup>3</sup>	ISO 1183
<b>Mechanical</b>			
Tensile Stress at Yield	150	MPa	ISO 527-2
Tensile Strain at Break	3	%	ISO 527-2
Flexural Modulus	7000	MPa	ISO 178
Flexural Stress	190	MPa	ISO 178
<b>Impact</b>			
Notched Izod Impact Strength	15	kJ/m <sup>2</sup>	ISO 180
<b>Thermal</b>			
Deflection Temperature Under Load Unannealed (0.45 MPa)	>200	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa)	215	°C	ISO 75-2/A
DSC Melting Point	221	°C	ISO 3146
<b>Electrical</b>			
Dielectric Strength, (2.00 mm)	34	kV/mm	IEC 60243-1
Comparative Tracking Index (CTI), (Solution A)	450	V	IEC 60112
Surface Resistivity	1E+15	ohm	IEC 60093
<b>Flammable</b>			
Burning Rate			
(2.00 mm)	<100	mm/min	ISO 3795
(2.00 mm)	<100	mm/min	FMVSS 302
<b>UL Information</b>			
Flame Rating	HB		UL 94

<b>Injection Parameters</b>	<b>Nominal Value</b>	<b>Units</b>
Drying Time	3.0 to 4.0	hr
Drying Temperature	80	°C
Processing (Melt) Temp	250 to 280	°C
Mold Temperature	60 to 100	°C