

Technical Data Sheet

Schulamid 612 HV H3 BLK968001

Polyamide 612

Product Description

Polyamide 612, high viscosity, heat stabilized for extrusion molding

Processing Method Extrusion**Resin ID** PA612

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density, (Method A)	1.05	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield			
(Type 1A, 50 mm/min)	63.0	MPa	ISO 527-2
(Type 1A, 50 mm/min) - Conditioned	49.0	MPa	ISO 527-2
Nominal Tensile Strain at Break, - Conditioned	>50	%	ISO 527-2
Flexural Modulus, (23 °C, 2.0 mm/min)	2700	MPa	ISO 178
Tensile Strain at Yield			
(Type 1A, 50 mm/min)	4.5	%	ISO 527-2
(Type 1A, 50 mm/min) - Conditioned	20	%	ISO 527-2
Tensile Modulus			
(1 mm/min, Type 1A)	2200	MPa	ISO 527-1
(1 mm/min, Type 1A) - Conditioned	1400	MPa	ISO 527-1
Flexural Stress, (2.0 mm/min, 3.5%)	85.0	MPa	ISO 178
Flexural Strength, (23 °C)	95.0	MPa	ASTM D790
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	5.0	kJ/m ²	ISO 179
(23 °C, Type 1, Edgewise, Notch A) - Conditioned	10	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	No Break		ISO 179
(-30 °C, Type 1, Edgewise)	No Break		ISO 179
(23 °C, Type 1, Edgewise) - Conditioned	No Break		ISO 179
Thermal			
Vicat Softening Temperature			
(B (50N), 50 °C/h)	180	°C	ISO 306
(A (10N), 50 °C/h)	210	°C	ISO 306

Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	140 °C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	60.0 °C	ISO 75-2/A
Flammable		
Burning Rate		
(2.00 mm)	<100 mm/min	ISO 3795
(2.00 mm)	<100 mm/min	FMVSS 302

Injection Parameters	Nominal Value	Units
Drying Time	3.0 to 4.0	hr
Drying Temperature	80	°C
Suggested Max Moisture	0.040 to 0.10	%
Processing (Melt) Temp	230 to 270	°C
Mold Temperature	50 to 90	°C