

Technical Data Sheet

Ferro Nylon RNY33MA14BK

Polyamide 66
LyondellBasell Industries
Engineering Plastics

General	
Filler / Reinforcement	• Glass Fiber, 33% Filler by Weight
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.40	1.40 g/cm ³	ASTM D792

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	24000 psi	165 MPa	ASTM D638
Tensile Elongation (Break)	5.0 %	5.0 %	ASTM D638
Flexural Modulus	1.40E+6 psi	9650 MPa	ASTM D790
Flexural Strength (Yield)	36000 psi	248 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.9 ft·lb/in	100 J/m	ASTM D256

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	505 °F	263 °C	
264 Psi (1.8 Mpa), Unannealed	490 °F	254 °C	

Technical Data Sheet

Ferro Nylon RNY33MA14BK

Polyamide 66
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Suggested Max Moisture	0.10 %	0.10 %
Rear Temperature	510 to 530 °F	266 to 277 °C
Middle Temperature	510 to 530 °F	266 to 277 °C
Front Temperature	510 to 530 °F	266 to 277 °C
Nozzle Temperature	500 to 540 °F	260 to 282 °C
Mold Temperature	150 to 180 °F	66 to 82 °C
Injection Pressure	500 to 1500 psi	3.45 to 10.3 MPa
Back Pressure	50.0 to 100 psi	0.345 to 0.689 MPa

Notes

These are typical property values not to be construed as specification limits.