



Technical Data Sheet

Matrixx 662E0

Polyamide 66
LyondellBasell Industries
Engineering Plastics

General

- | | |
|-------------------|---------------------|
| Forms | • Pellets |
| Processing Method | • Injection Molding |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.14	1.14 g/cm ³	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	11500 psi	79.3 MPa	ASTM D638
Flexural Modulus - Tangent	425000 psi	2930 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	1.1 ft·lb/in	59 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	385 °F	196 °C	
264 Psi (1.8 Mpa), Unannealed	158 °F	70.0 °C	

Technical Data Sheet

Matrixx 662E0

Polyamide 66
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	160 to 180 °F	71 to 82 °C
Drying Time	4.0 hr	4.0 hr
Rear Temperature	480 to 560 °F	249 to 293 °C
Middle Temperature	480 to 560 °F	249 to 293 °C
Front Temperature	480 to 560 °F	249 to 293 °C
Processing (Melt) Temp	520 to 560 °F	271 to 293 °C
Mold Temperature	125 to 180 °F	52 to 82 °C
Injection Rate	Moderate-Fast	Moderate-Fast
Back Pressure	< 100 psi	< 0.689 MPa
Cushion	0.125 to 0.250 in	3.18 to 6.35 mm

Injection Notes

- 20°C Dewpoint
- Screw Speed: Medium

Notes

These are typical property values not to be construed as specification limits.