



Technical Data Sheet

Matrixx F662E15

Polyamide 66
 LyondellBasell Industries
 Engineering Plastics

Product Description

15% glass reinforced Nylon 6,6

General

Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Density / Specific Gravity	1.22	1.22 g/cm ³	ASTM D792
----------------------------	------	------------------------	-----------

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Tensile Strength (Yield)	15300 psi	106 MPa	ASTM D638
Tensile Elongation (Yield)	9.0 %	9.0 %	ASTM D638
Flexural Modulus	724000 psi	5000 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
--------	-------------------------	--------------------	-------------

Notched Izod Impact	0.67 ft·lb/in	36 J/m	ASTM D256
---------------------	---------------	--------	-----------

Technical Data Sheet

Matrixx F662E15

Polyamide 66
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	160 to 180 °F	71 to 82 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Rear Temperature	480 to 520 °F	249 to 271 °C
Middle Temperature	480 to 520 °F	249 to 271 °C
Front Temperature	480 to 540 °F	249 to 282 °C
Processing (Melt) Temp	500 to 540 °F	260 to 282 °C
Mold Temperature	150 to 200 °F	66 to 93 °C
Injection Rate	Moderate-Fast	Moderate-Fast
Back Pressure	< 50.0 psi	< 0.345 MPa
Cushion	0.250 to 0.500 in	6.35 to 12.7 mm

Injection Notes

Dessicant dryer with -20°F dewpoint
Screw Speed: Slow to Medium

Notes

These are typical property values not to be construed as specification limits.