

Technical Data Sheet

Matrixx F663E13

Polyamide 66
LyondellBasell Industries
Engineering Plastics

General

- | | |
|------------------------|-------------------------------------|
| Filler / Reinforcement | • Glass Fiber, 13% Filler by Weight |
| Forms | • Pellets |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Density / Specific Gravity	1.22	1.22 g/cm ³	ASTM D792
----------------------------	------	------------------------	-----------

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Tensile Strength (Yield)	16500 psi	114 MPa	ASTM D638
--------------------------	-----------	---------	-----------

Flexural Modulus - Tangent	720000 psi	4960 MPa	ASTM D790
----------------------------	------------	----------	-----------

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
--------	-------------------------	--------------------	-------------

Notched Izod Impact	1.0 ft·lb/in	53 J/m	ASTM D256
---------------------	--------------	--------	-----------

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
---------	-------------------------	--------------------	-------------

Deflection Temperature Under Load			ASTM D648
-----------------------------------	--	--	-----------

264 Psi (1.8 Mpa), Unannealed	460 °F	238 °C	
-------------------------------	--------	--------	--

RTI Str	150 °F	65.6 °C	UL 746B
---------	--------	---------	---------

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
--------------	-------------------------	--------------------	-------------

Flame Rating (0.06 In (1.5 Mm))	HB	HB	UL 94
---------------------------------	----	----	-------

Technical Data Sheet

Matrixx F663E13

Polyamide 66
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	160 to 200 °F	71 to 93 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Rear Temperature	520 to 570 °F	271 to 299 °C
Middle Temperature	520 to 570 °F	271 to 299 °C
Front Temperature	520 to 570 °F	271 to 299 °C
Processing (Melt) Temp	530 to 570 °F	277 to 299 °C
Mold Temperature	150 to 200 °F	66 to 93 °C
Injection Rate	Moderate-Fast	Moderate-Fast
Back Pressure	< 50.0 psi	< 0.345 MPa
Cushion	0.250 to 0.500 in	6.35 to 12.7 mm

Injection Notes

- Screw Speed: Slow to Medium
- Dessicant dryer with -20°F dewpoint

Notes

These are typical property values not to be construed as specification limits.