



Technical Data Sheet

# Qr Resin QR-9066

Polyamide 66  
LyondellBasell Industries  
Engineering Plastics

**General**

Appearance	• Black	• Colors Available	• Natural Color
Forms	• Pellets		

**Physical**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.13	1.13 g/cm <sup>3</sup>	ASTM D792

**Mechanical**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Break)	11200 psi	77.2 MPa	ASTM D638
Tensile Elongation (Break)	40 %	40 %	ASTM D638
Flexural Modulus	396000 psi	2730 MPa	ASTM D790

**Impact**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	1.0 ft·lb/in	53 J/m	ASTM D256

**Thermal**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 Psi (1.8 Mpa), Unannealed	160 °F	71.1 °C	ASTM D648
Melting Temperature	513 °F	267 °C	

Technical Data Sheet

# Qr Resin QR-9066

Polyamide 66  
LyondellBasell Industries  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	140 °F	60 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Drying Time, Maximum	4.0 hr	4.0 hr
Rear Temperature	500 to 550 °F	260 to 288 °C
Middle Temperature	500 to 550 °F	260 to 288 °C
Front Temperature	520 to 550 °F	271 to 288 °C
Nozzle Temperature	530 to 580 °F	277 to 304 °C
Processing (Melt) Temp	530 to 580 °F	277 to 304 °C
Mold Temperature	150 to 200 °F	66 to 93 °C

**Notes**

These are typical property values not to be construed as specification limits.