

## Technical Data Sheet

# Schulamid 66 GF 15 H

Polyamide 66  
LyondellBasell Industries  
Engineering Plastics

### Product Description

15% glass fiber reinforced, heat stabilized Polyamide 66

### General

Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight		
Features	• Good Surface Finish • Heat Aging Resistant	• Medium Viscosity • Oil Resistant	
UL File Number	• E86615		
Processing Method	• Injection Molding		

Physical	Dry	Conditioned	Unit	Test Method
Density	1.23	--	g/cm <sup>3</sup>	ISO 1183/A
Water Absorption				ISO 62
Equilibrium, 73°F (23°C), 50% Rh	2.2	--	%	
Viscosity Number	140	--	cm <sup>3</sup> /g	ISO 307

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	899000 (6200)	522000 (3600)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Break)	17400 (120)	10900 (75.0)	psi (MPa)	ISO 527-2/1A/5
Tensile Strain (Break)	3.0	12	%	ISO 527-2/1A/5
Flexural Modulus	711000 (4900)	--	psi (MPa)	ISO 178
Flexural Stress	23900 (165)	--	psi (MPa)	ISO 178
Flexural Strain at Flexural Strength	4.0	--	%	ISO 178

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F (-30°C)	2.4 (5.0)	--	ft-lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
73°F (23°C)	2.9 (6.0)	4.3 (9.0)	ft-lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F (-30°C)	13 (28)	--	ft-lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
73°F (23°C)	14 (30)	33 (70)	ft-lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	

Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness (H 358/30)	24700 (170)	16000 (110)	psi (MPa)	ISO 2039-1

Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
66 Psi (0.45 Mpa), Unannealed	> 482 (> 250)	--	°F (°C)	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	455 (235)	--	°F (°C)	ISO 75-2/Af

## Technical Data Sheet

# Schulamid 66 GF 15 H

Polyamide 66  
LyondellBasell Industries  
Engineering Plastics

Thermal	Dry	Conditioned	Unit	Test Method
Vicat Softening Temperature				
--	473 (245)	--	°F (°C)	ISO 306/B50
--	> 482 (> 250)	--	°F (°C)	ISO 306/A50
Ball Pressure Test (230°F (110°C))	Pass	--		IEC 60695-10-2
RTI Elec				UL 746B
0.030 In (0.75 Mm)	248 (120)	--	°F (°C)	
0.06 In (1.5 Mm)	248 (120)	--	°F (°C)	
0.12 In (3.0 Mm)	248 (120)	--	°F (°C)	
RTI Imp				UL 746B
0.030 In (0.75 Mm)	212 (100)	--	°F (°C)	
0.06 In (1.5 Mm)	230 (110)	--	°F (°C)	
0.12 In (3.0 Mm)	248 (120)	--	°F (°C)	
RTI Str				UL 746B
0.030 In (0.75 Mm)	230 (110)	--	°F (°C)	
0.06 In (1.5 Mm)	248 (120)	--	°F (°C)	
0.12 In (3.0 Mm)	266 (130)	--	°F (°C)	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	> 1.0E+15	> 1.0E+12	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	> 1.0E+10	ohms·m	IEC 62631-3-1
Comparative Tracking Index	450	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate				
0.0787 In (2.00 Mm)	1.6 (40)	--	in/min (mm/min)	ISO 3795
0.0787 In (2.00 Mm)	1.6 (40)	--	in/min (mm/min)	FMVSS 302
Flammability Classification				IEC 60695-11-10, -20
0.030 In (0.75 Mm)	HB	--		
0.06 In (1.5 Mm)	HB	--		
0.12 In (3.0 Mm)	HB	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.06 In (1.5 Mm)	1200 (650)	--	°F (°C)	
0.12 In (3.0 Mm)	1200 (650)	--	°F (°C)	

Technical Data Sheet

**Schulamid 66 GF 15 H**

Polyamide 66  
LyondellBasell Industries  
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	536 to 572 °F	280 to 300 °C
Mold Temperature	140 to 248 °F	60 to 120 °C

**Notes**

These are typical property values not to be construed as specification limits.