

Technical Data Sheet

# Schulamid 66 GF 30 H EP

Polyamide 66  
LyondellBasell Industries  
Engineering Plastics

**Product Description**

30% glass fiber reinforced, heat stabilized Polyamide 66 with excellent stiffness and impact strength.

**General**

- |                        |                                     |
|------------------------|-------------------------------------|
| Filler / Reinforcement | • Glass Fiber, 30% Filler by Weight |
| Processing Method      | • Injection Molding                 |

Physical	Dry	Conditioned	Unit	Test Method
Density	1.35	--	g/cm <sup>3</sup>	ISO 1183/A
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	1.41E+6 (9700)	972000 (6700)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Break)	25400 (175)	17400 (120)	psi (MPa)	ISO 527-2/1A/5
Tensile Strain (Break)	3.2	5.0	%	ISO 527-2/1A/5
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°f (-30°c)	3.3 (7.0)	3.3 (6.9)	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
73°f (23°c)	6.2 (13)	7.6 (16)	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°f (-30°c)	31 (66)	29 (60)	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
73°f (23°c)	40 (85)	43 (90)	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
66 Psi (0.45 Mpa), Unannealed	> 482 (> 250)	--	°F (°C)	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	473 (245)	--	°F (°C)	ISO 75-2/Af
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate				
0.0787 In (2.00 Mm)	1.2 (30)	--	in/min (mm/min)	ISO 3795
0.0787 In (2.00 Mm)	1.2 (30)	--	in/min (mm/min)	FMVSS 302

Technical Data Sheet

# Schulamid 66 GF 30 H EP

Polyamide 66  
LyondellBasell Industries  
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	536 to 572 °F	280 to 300 °C
Mold Temperature	140 to 248 °F	60 to 120 °C

**Notes**

These are typical property values not to be construed as specification limits.