

Technical Data Sheet

Schulamid 66 GF 30 HR

Polyamide 66
LyondellBasell Industries
Engineering Plastics

Product Description
30% glass fiber reinforced, hydrolysis resistant Polyamide 66

General			
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Features	• Fuel Resistant • Good Glycol Resistance	• Good Processability • Medium Viscosity	• Oil Resistant
Automotive Specifications	• FORD WSK-M4D752-A	• FORD WSK-M4D752-A Color: Black	• FORD WSK-M4D752-A Color: 31 Black
Processing Method	• Injection Molding		

Physical	Dry	Conditioned	Unit	Test Method
Density	1.36	--	g/cm ³	ISO 1183/A
Viscosity Number	140	--	cm ³ /g	ISO 307

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	1.45E+6 (10000)	1.02E+6 (7000)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Break)	26100 (180)	16700 (115)	psi (MPa)	ISO 527-2/1A/5
Tensile Strain (Break)	3.0	6.0	%	ISO 527-2/1A/5

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°f (-30°c)	3.3 (7.0)	--	ft·lb/in ² (kJ/m ²)	
73°f (23°c)	4.3 (9.0)	7.6 (16)	ft·lb/in ² (kJ/m ²)	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°f (-30°c)	26 (55)	--	ft·lb/in ² (kJ/m ²)	
73°f (23°c)	36 (75)	40 (85)	ft·lb/in ² (kJ/m ²)	

Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
66 Psi (0.45 Mpa), Unannealed	> 482 (> 250)	--	°F (°C)	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	473 (245)	--	°F (°C)	ISO 75-2/Af
Vicat Softening Temperature	> 482 (> 250)	--	°F (°C)	ISO 306/B50 ISO 306/A50

Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	> 1.0E+15	--	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	> 1.0E+10	ohms·m	IEC 62631-3-1



Technical Data Sheet

Schulamid 66 GF 30 HR

Polyamide 66
 LyondellBasell Industries
 Engineering Plastics

Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate				
0.0787 In (2.00 Mm)	1.4 (35)	--	in/min (mm/min)	ISO 3795
0.0787 In (2.00 Mm)	1.4 (35)	--	in/min (mm/min)	FMVSS 302

Technical Data Sheet

Schulamid 66 GF 30 HR

Polyamide 66
LyondellBasell Industries
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	536 to 572 °F	280 to 300 °C
Mold Temperature	140 to 248 °F	60 to 120 °C

Notes

These are typical property values not to be construed as specification limits.