

Technical Data Sheet

# SCHULAMID® 66 SK 2000

Polyamide 66  
Engineering Plastics

**Product Description**

Extrem high impact Polyamide 66

**General**

Features	<ul style="list-style-type: none"> <li>• Low Temperature Toughness</li> <li>• Medium Viscosity</li> </ul>	<ul style="list-style-type: none"> <li>• Oil Resistant</li> <li>• Ultra High Impact Resistance</li> </ul>	<ul style="list-style-type: none"> <li>• Ultra High Toughness</li> </ul>
Automotive Specifications	<ul style="list-style-type: none"> <li>• FORD WSK-M4D666-A Color: Black</li> <li>• FORD WSS-M4D666-A2 Color: Black</li> </ul>	<ul style="list-style-type: none"> <li>• GM GMW15702-013051 PA66-I Color: Natural</li> <li>• GM GMW15702-013051 PA66-I Color: 96.8001 Black</li> </ul>	
UL File Number	<ul style="list-style-type: none"> <li>• E86615</li> </ul>		
Processing Method	<ul style="list-style-type: none"> <li>• Injection Molding</li> </ul>		
Resin ID (ISO 1043)	<ul style="list-style-type: none"> <li>• PA66I</li> </ul>		

Physical	Dry	Conditioned	Unit	Test Method
Density	1.06	--	g/cm <sup>3</sup>	ISO 1183/A
Water Absorption				ISO 62
Equilibrium, 73°F (23°C), 50% RH	2.0	--	%	

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	261000 (1800)	87000 (600)	psi (MPa)	ISO 527-2/1A/1
Tensile Stress (Yield)	7250 (50.0)	4350 (30.0)	psi (MPa)	ISO 527-2/1A/50
Tensile Strain (Yield)	6.0	32	%	ISO 527-2/1A/50
Nominal Tensile Strain at Break	> 40	> 100	%	ISO 527-2/1A/50
Flexural Modulus <sup>1</sup>	239000 (1650)	--	psi (MPa)	ISO 178
Flexural Stress <sup>1</sup>	8990 (62.0)	--	psi (MPa)	ISO 178
Flexural Strain at Flexural Strength	7.0	--	%	ISO 178

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F (-30°C)	12 (25)	--	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
73°F (23°C)	38 (80)	55 (120)	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F (-30°C)	No Break	--		
73°F (23°C)	No Break	No Break		

Technical Data Sheet

# SCHULAMID® 66 SK 2000

Polyamide 66  
Engineering Plastics

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
66 psi (0.45 MPa), Unannealed	275 (135)	--	°F (°C)	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	140 (60.0)	--	°F (°C)	ISO 75-2/Af
Vicat Softening Temperature				
--	> 482 (> 250)	--	°F (°C)	ISO 306/A50
--	347 (175)	--	°F (°C)	ISO 306/B50
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate				
0.0787 in (2.00 mm)	1.5 (38)	--	in/min (mm/min)	ISO 3795
0.0787 in (2.00 mm)	1.5 (38)	--	in/min (mm/min)	FMVSS 302
Flammability Classification				IEC 60695-11-10, -20
0.06 in (1.5 mm)	HB	--		
0.12 in (3.0 mm)	HB	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.06 in (1.5 mm)	--	1110 (600)	°F (°C)	
0.12 in (3.0 mm)	--	1110 (600)	°F (°C)	

Technical Data Sheet

**SCHULAMID® 66 SK 2000**

Polyamide 66  
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Suggested Max Regrind	20 %	20 %
Processing (Melt) Temp	518 to 554 °F	270 to 290 °C
Mold Temperature	140 to 212 °F	60 to 100 °C

**Notes**

<sup>1</sup> 0.079 in/min (2.0 mm/min)

**Notes**

These are typical property values not to be construed as specification limits.