

Technical Data Sheet

Schulamid 66 GBF3020 FR4 BLK 968001



Polyamide 66

Product Description

30% glass fibre and glass beads reinforced flame-retardant Polyamide 66 grade with low warpage high mechanical stability and high dimension stability, without PBDE

| | |
|-----------------------------|-----------------------------|
| Processing Method | Injection Molding |
| Attribute | Low Warpage |
| Additive | Flame Retardant |
| Filler/Reinforcement | Glass Bead\Glass Fiber, 30% |
| Resin ID | PA66 |

| Typical Properties | Nominal Value | Units | Test Method |
|--|---------------|-------------------|----------------|
| Physical | | | |
| Density, (Method A) | 1.59 | g/cm ³ | ISO 1183 |
| Mechanical | | | |
| Tensile Strain at Break | | | |
| (Type 1A, 5 mm/min) | 2.5 | % | ISO 527-2 |
| (Type 1A, 5 mm/min) - Conditioned | 4.5 | % | ISO 527-2 |
| Tensile Stress at Break | | | |
| (Type 1A, 5 mm/min) | 140 | MPa | ISO 527-2 |
| (Type 1A, 5 mm/min) - Conditioned | 92.0 | MPa | ISO 527-2 |
| Tensile Modulus | | | |
| (1 mm/min, Type 1A) | 8700 | MPa | ISO 527-1 |
| (1 mm/min, Type 1A) - Conditioned | 5000 | MPa | ISO 527-1 |
| Impact | | | |
| Charpy Impact Strength - Notched | | | |
| (23 °C, Type 1, Edgewise, Notch A) | 5.5 | kJ/m ² | ISO 179 |
| (-30 °C, Type 1, Edgewise, Notch A) | 4.5 | kJ/m ² | ISO 179 |
| (23 °C, Type 1, Edgewise, Notch A) - Conditioned | 7.0 | kJ/m ² | ISO 179 |
| Charpy Impact Strength - Unnotched | | | |
| (23 °C, Type 1, Edgewise) | 42 | kJ/m ² | ISO 179 |
| (-30 °C, Type 1, Edgewise) | 38 | kJ/m ² | ISO 179 |
| (23 °C, Type 1, Edgewise) - Conditioned | 51 | kJ/m ² | ISO 179 |
| Hardness | | | |
| Ball Pressure Test, (200 °C) | Pass | | IEC 60695-10-2 |
| Thermal | | | |

| | | |
|---|---------|------------|
| Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise) | >250 °C | ISO 75-2/B |
| Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise) | 224 °C | ISO 75-2/A |
| RTI Elec | | |
| (1.5 mm) | 65.0 °C | UL 746B |
| (3.0 mm) | 65.0 °C | UL 746B |
| RTI Imp | | |
| (1.5 mm) | 65.0 °C | UL 746B |
| (3.0 mm) | 65.0 °C | UL 746B |
| RTI Str | | |
| (1.5 mm) | 65.0 °C | UL 746B |
| (3.0 mm) | 65.0 °C | UL 746B |

Electrical

| | | |
|--|----------------|---------------|
| Volume Resistivity | >9.9E+13 ohm*m | IEC 62631-3-1 |
| Dissipation Factor, (100 Hz) | 0.049 | IEC 60250 |
| Dielectric Strength | 22 kV/mm | IEC 60243-1 |
| Comparative Tracking Index (CTI), (Solution A) | 175 V | IEC 60112 |
| Surface Resistivity | >7.8E+12 ohm | IEC 60093 |
| Relative Permittivity | | |
| (100 Hz) | 4.81 | IEC 60250 |
| (1 MHz) | 3.85 | IEC 60250 |

Flammable

| | | |
|---|------------|----------------|
| Burning Rate, (2.00 mm, Self-Extinguishing) | 0.0 mm/min | ISO 3795 |
| Glow Wire Flammability Index | | |
| (1.5 mm) | 960 °C | IEC 60695-2-12 |
| (3.0 mm) | 960 °C | IEC 60695-2-12 |
| Glow Wire Ignition Temperature | | |
| (1.5 mm) | 750 °C | IEC 60695-2-13 |
| (3.0 mm) | 750 °C | IEC 60695-2-13 |
| Oxygen Index | 38 % | ISO 4589-2 |

UL Information

| | | |
|------------------------------------|--------|----------------------|
| Flame Rating | | |
| (1.5 mm) | V-0 | UL 94 |
| (3.0 mm) | V-0 | UL 94 |
| Flammability Classification | | |
| (1.5 mm) | V-0 | IEC 60695-11-10, -20 |
| (3.0 mm) | V-0 | IEC 60695-11-10, -20 |
| UL File Number | E86615 | |

| Injection Parameters | Nominal Value | Units |
|-----------------------------|----------------------|--------------|
| Drying Time | 4.0 to 6.0 | hr |
| Drying Temperature | 80 | °C |
| Suggested Max Moisture | 0.040 to 0.10 | % |
| Screw Speed | <250 | mm/sec |
| Processing (Melt) Temp | 270 to 300 | °C |
| Injection Rate | Slow-Moderate | |
| Back Pressure | 20 to 80 | bar |
| Mold Temperature | 60 to 90 | °C |