

## Technical Data Sheet

**Schulamid 66 MK20 HI BLK968001**

Polyamide 66

**Product Description**

20% mineral filled PA 66, impact modified

<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Impact Modified
<b>Additive</b>	Impact Modifier
<b>Filler/Reinforcement</b>	Mineral, 20%

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Density, (Method A)	1.28	g/cm <sup>3</sup>	ISO 1183
<b>Mechanical</b>			
Tensile Strain at Break			
(Type 1A, 5 mm/min)	12	%	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	16	%	ISO 527-2
Tensile Stress at Break			
(Type 1A, 5 mm/min)	70.0	MPa	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	45.0	MPa	ISO 527-2
Tensile Modulus			
(1 mm/min, Type 1A)	3500	MPa	ISO 527-1
(1 mm/min, Type 1A) - Conditioned	2000	MPa	ISO 527-1
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	8.0	kJ/m <sup>2</sup>	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	6.0	kJ/m <sup>2</sup>	ISO 179
(23 °C, Type 1, Edgewise, Notch A) - Conditioned	14	kJ/m <sup>2</sup>	ISO 179
(-30 °C, Type 1, Edgewise, Notch A) - Conditioned	5.0	kJ/m <sup>2</sup>	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	130	kJ/m <sup>2</sup>	ISO 179
(-30 °C, Type 1, Edgewise)	120	kJ/m <sup>2</sup>	ISO 179
(23 °C, Type 1, Edgewise) - Conditioned	No Break		ISO 179
(-30 °C, Type 1, Edgewise) - Conditioned	170	kJ/m <sup>2</sup>	ISO 179
<b>Hardness</b>			
Ball Indentation Hardness, (H 358/30)	170	MPa	ISO 2039-1
Ball Pressure Test, (100 °C)	Pass		IEC 60695-10-2
<b>Thermal</b>			

Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	170	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	90.0	°C	ISO 75-2/A
<b>Electrical</b>			
Volume Resistivity	>1.0E+13	ohm*m	IEC 62631-3-1
- Conditioned	10000000000	ohm*m	IEC 62631-3-1
Comparative Tracking Index (CTI)	550	V	IEC 60112
Surface Resistivity	>1.0E+15	ohm	IEC 60093
<b>Flammable</b>			
Burning Rate			
(2.00 mm)	<100	mm/min	ISO 3795
(2.00 mm)	<100	mm/min	FMVSS 302
<b>UL Information</b>			
Flammability Classification, (3.2 mm)	HB		IEC 60695-11-10, -20

<b>Injection Parameters</b>	<b>Nominal Value</b>	<b>Units</b>
Drying Time	3.0 to 4.0	hr
Drying Temperature	80	°C
Suggested Max Moisture	0.040 to 0.10	%
Processing (Melt) Temp	280 to 300	°C
Mold Temperature	60 to 120	°C