

Technical Data Sheet

**Schulamid F662E33BKBLK**



Polyamide 66

**Product Description**

Schulamid F662E33BKBLK is a Polyamide 66 Glass Fiber, 33% filled material and is typically used in Injection Molding applications.

<b>Processing Method</b>	Injection Molding
<b>Forms</b>	Pellets
<b>Appearance</b>	Black
<b>Application</b>	Industrial Applications
<b>Filler/Reinforcement</b>	Glass Fiber, 33%

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Density - Specific Gravity	1.38	g/cm <sup>3</sup>	ASTM D792
<b>Mechanical</b>			
Tensile Strength at Yield	159	MPa	ASTM D638
Flexural Modulus, (Tangent)	8270	MPa	ASTM D790
<b>Impact</b>			
Notched Izod Impact	69	J/m	ASTM D256
<b>Thermal</b>			
Deflection Temperature Under Load Unannealed (264 psi)	249	°C	ASTM D648
RTI Str	65.6	°C	UL 746B
<b>UL Information</b>			
Flame Rating, (1.5 mm)	HB		UL 94

Injection Parameters	Nominal Value	Units
Drying Time	4.0 to 6.0	hr
Drying Temperature	71 to 93	°C
Processing (Melt) Temp	277 to 299	°C
Front Temperature	271 to 299	°C
Middle Temperature	271 to 299	°C
Rear Temperature	271 to 299	°C
Injection Rate	Moderate-Fast	
Back Pressure	<0.345	MPa
Mold Temperature	66 to 93	°C
Cushion	6.35 to 12.7	mm