

## Technical Data Sheet

### *Schulamid* F662E33NANAT



Polyamide 66

#### Product Description

*Schulamid* F662E33NANAT is a Polyamide 66 Glass Fiber, 33% filled material and is typically used in Injection Molding applications.

|                             |                         |
|-----------------------------|-------------------------|
| <b>Processing Method</b>    | Injection Molding       |
| <b>Forms</b>                | Pellets                 |
| <b>Appearance</b>           | Black                   |
| <b>Application</b>          | Industrial Applications |
| <b>Filler/Reinforcement</b> | Glass Fiber, 33%        |

| Typical Properties                                     | Nominal Value | Units             | Test Method |
|--|---------------|-------------------|-------------|
| <b>Physical</b>  |               |                   |             |
| Density - Specific Gravity                             | 1.38          | g/cm <sup>3</sup> | ASTM D792   |
| <b>Mechanical</b>                                      |               |                   |             |
| Tensile Strength at Yield                              | 159           | MPa               | ASTM D638   |
| Flexural Modulus, (Tangent)                            | 8270          | MPa               | ASTM D790   |
| <b>Impact</b>  |               |                   |             |
| Notched Izod Impact                                    | 69            | J/m               | ASTM D256   |
| <b>Thermal</b>   |               |                   |             |
| Deflection Temperature Under Load Unannealed (264 psi) | 249           | °C                | ASTM D648   |
| RTI Str  | 65.6          | °C                | UL 746B     |
| <b>UL Information</b>                                  |               |                   |             |
| Flame Rating, (1.5 mm)                                 | HB            |                   | UL 94       |

| Injection Parameters   | Nominal Value | Units |
|------------------------|---------------|-------|
| Drying Time            | 4.0 to 6.0    | hr    |
| Drying Temperature     | 71 to 93      | °C    |
| Processing (Melt) Temp | 277 to 299    | °C    |
| Front Temperature      | 271 to 299    | °C    |
| Middle Temperature     | 271 to 299    | °C    |
| Rear Temperature       | 271 to 299    | °C    |
| Injection Rate         | Moderate-Fast |       |
| Back Pressure          | <0.345        | MPa   |
| Mold Temperature       | 66 to 93      | °C    |
| Cushion                | 6.35 to 12.7  | mm    |