

## Technical Data Sheet

### *Schulamid* FPI66-G33/HS/UV BKBLK



Polyamide 66

#### Product Description

*Schulamid* FPI66-G33/HS/UV BKBLK is a Polyamide 66 Glass Fiber, 33% filled material.

<b>Forms</b>	Pellets
<b>Appearance</b>	Black
<b>Filler/Reinforcement</b>	Glass Fiber, 33%

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Density - Specific Gravity	1.39	g/cm <sup>3</sup>	ASTM D792
<b>Mechanical</b>			
Tensile Strength, (23 °C)	155	MPa	ASTM D638
Flexural Modulus, (23 °C, Secant)	9200	MPa	ASTM D790
Flexural Strength, (23 °C)	235	MPa	ASTM D790
<b>Impact</b>			
Notched Izod Impact, (23 °C, 3.18 mm)	69	J/m	ASTM D256