

## Technical Data Sheet

**Vitamide AS10BK 2-0400**

Polyamide 66

**Product Description**

General purpose, Medium viscosity, Lubricated Polyamide 66. Suitable for a wide range of applications this grade offers an effective cycle time and a good balance of stiffness and impact strength. Available with enhanced UV (AS20), heat stability (AS30) and cycle time performance (AS40). Colour matched compounds and customer specific performance requirements are available on request. Listed as V2 under UL File Reference E132739

**Processing Method** Injection Molding

<b>Typical Properties</b>	<b>Nominal Value</b>	<b>Units</b>	<b>Test Method</b>
<b>Physical</b>			
Density	1.13	g/cm <sup>3</sup>	ISO 1183
<b>Mechanical</b>			
Tensile Strain at Break	40	%	ISO 527-2
Flexural Modulus	2900	MPa	ISO 178
Tensile Stress at Break	85	MPa	ISO 527-2
Flexural Stress	105	MPa	ISO 178
<b>Impact</b>			
Charpy Impact Strength - Notched, (23 °C, Type 1, Edgewise, Notch A)	4.5	kJ/m <sup>2</sup>	ISO 179
Notched Izod Impact Strength	5	kJ/m <sup>2</sup>	ISO 180
<b>Hardness</b>			
Shore Hardness, (Shore D)	84		ISO 868
Rockwell Hardness, (R-Scale)	120		ISO 2039-2
Ball Indentation Hardness	155	MPa	ISO 2039-1
<b>Thermal</b>			
Vicat Softening Temperature, (B (50N), 120 °C/h)	198	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa)	223	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa)	80	°C	ISO 75-2/A
Melting Temperature	260	°C	ISO 11357-3
<b>Electrical</b>			
Dielectric Strength	27	kV/mm	ASTM D149
Comparative Tracking Index (CTI)	600	V	IEC 60112
Surface Resistivity	1E+16	ohm	ASTM D257
<b>Flammable</b>			
Burning Rate	100	mm/min	ISO 3795
Glow Wire Flammability Index	850	°C	IEC 60695-2-12
<b>Additional Information</b>			

Molding Shrinkage	1.5 %	ISO 294-4
Water Absorption 23C/50RH	2.3 %	ISO 62
Water Absorption 24h/23C	1.5 %	ISO 62
Water Absorption Sat/23C	8.5 %	ISO 62

**UL Information**

Flame Rating	V-2	UL 94
--------------	-----	-------

<b>Injection Parameters</b>	<b>Nominal Value</b>	<b>Units</b>
Drying Time	3.0 to 4.0	hr
Drying Temperature	80	°C
Processing (Melt) Temp	270 to 290	°C
Mold Temperature	60 to 100	°C