

Technical Data Sheet

# Icorene N9302

Polybutylene Terephthalate  
LyondellBasell Industries  
Custom Powders

## Product Description

ICORENE® N9302 is based on a high flow grade PBT designed for injection moulding and extrusion.

ICORENE® N9302 is available as a powder suitable for use in making masterbatch or compounds.

ICORENE® N9302 is not intended for use in medical or pharmaceutical applications.

## General

Forms • Powder

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.30 g/cm <sup>3</sup>	1.30 g/cm <sup>3</sup>	ISO 1183
Melt Volume-Flow Rate (MVR) (250°C/2.16 Kg)	45 cm <sup>3</sup> /10min	45 cm <sup>3</sup> /10min	ISO 1133
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Melting Temperature	437 °F	225 °C	DSC

## Notes

These are typical property values not to be construed as specification limits.