

Technical Data Sheet

# Matrixx 35S5151

Polybutylene Terephthalate  
LyondellBasell Industries  
Engineering Plastics

General	
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Additive	• Flame Retardant
Features	• Flame Retardant
Forms	• Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.50	1.50 g/cm <sup>3</sup>	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	13000 psi	89.6 MPa	ASTM D638
Flexural Modulus	700000 psi	4830 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	0.80 ft·lb/in	43 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	400 °F	204 °C	
264 Psi (1.8 Mpa), Unannealed	360 °F	182 °C	
RTI Elec	167 °F	75.0 °C	UL 746B
RTI Imp	167 °F	75.0 °C	UL 746B
RTI Str	167 °F	75.0 °C	UL 746B
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating			UL 94
0.06 In (1.5 Mm)	V-0	V-0	
0.10 In (2.5 Mm)	5VA	5VA	

**Notes**

These are typical property values not to be construed as specification limits.